




Kyocera Ceramic Chip Capacitors are available for different applications as classified below:

Series	Dielectric Options	Typical Applications	Features	Terminations	Available Size
CM	C0G (NP0) X5R X7R *X6S *X7S Y5V	General purpose	Wide cap range	Nickel barrier	01005, 0201, 0402 0603, 0805, 1206 1210, 1812
CT	X5R X7R Y5V	IC card (Decoupling)	Low profile	Nickel barrier	0201, 0402, 0603 0805, 1206, 1210
CA	C0G (NP0) X5R, X7R	Digital signal Pass line	Reduction in placing cost	Nickel barrier	0405, 0508
CL	X7S	ICs (Decoupling)	Low inductance	Nickel barrier	0204, 0306
CF	C0G (NP0) X7R	High voltage & Power circuits	High voltage 250VDC, 630VDC 1000VDC, 2000VDC 3000VDC, 4000VDC	Nickel barrier	0805, 1206, 1210 1812, 2208, 1808 2220
DM	X7R	Automotive	Thermal shock Resistivity High reliability	Nickel barrier	0603,0805,1206

\* Option  
\* Negative temperature coefficient dielectric types are available on request.

## Dimensions



## Dimensions and Packaging Quantities

Size	Code		Dimension Code	Dimensions (mm)						Maximum quantity per reel	
	JIS	EIA		L	W	T	P min.	P max.	P to P min.	φ180 Reel	φ330 Reel
02	0402	01005	A	0.4±0.02	0.2±0.02	0.2±0.02	0.07	0.14	0.13	40kp (E4/1) 20kp (P8/2)	-
03	0603	0201	A	0.6±0.03	0.3±0.03	0.22 max.	0.10	0.20	0.20	30kp (P8/1) 15kp (P8/2)	150kp (P8/1) 50kp (P8/2)
			B			0.3±0.03				30kp (P8/1) 15kp (P8/2)	150kp (P8/1) 50kp (P8/2)
			C	0.6±0.05	0.3±0.05	0.3±0.05	0.13	0.23	0.19	30kp (P8/1) 15kp (P8/2)	150kp (P8/1) 50kp (P8/2)
			D	0.6±0.09	0.3±0.09	0.3±0.09	0.10	0.20	0.20	15kp (P8/2)	-
			E			0.25 max.				15kp (P8/2)	-
05	1005	0402	A	1.0±0.05	0.5±0.05	0.25 max.	0.15	0.35	0.30	20kp (P8/1) 10kp (P8/2)	100kp (P8/1) 50kp (P8/2)
			B			0.33 max.				10kp (P8/2)	-
			C			0.35 max.				20kp (P8/1) 10kp (P8/2)	100kp (P8/1) 50kp (P8/2)
			D			0.5±0.05				20kp (P8/1) 10kp (P8/2)	100kp (P8/1) 50kp (P8/2)
			E	1.0±0.10	0.5±0.10	0.35 max.				20kp (P8/1) 10kp (P8/2)	100kp (P8/1) 50kp (P8/2)
			F			0.5±0.10				20kp (P8/1) 10kp (P8/2)	50kp (P8/2)
			G			0.5±0.15				20kp (P8/1) 10kp (P8/2)	50kp (P8/2)
			H			0.5±0.15				20kp (P8/1) 10kp (P8/2)	50kp (P8/2)
105	1608	0603	A	1.6±0.10	0.8±0.10	0.55 max.	0.20	0.60	0.50	4kp (P8/4) 8kp (P8/2)	10kp (P8/4) 20kp (P8/2)
			B			0.8±0.10				4kp (P8/4)	10kp (P8/4)
			C	1.6±0.15	0.8±0.15	0.55 max.				8kp (P8/2) 4kp (P8/4)	20kp (P8/2) 10kp (P8/4)
			D			0.8±0.15				8kp (P8/2) 4kp (P8/4)	20kp (P8/2) 10kp (P8/4)
			E	1.6±0.2	0.8±0.2	0.55 max.				8kp (P8/2) 4kp (P8/4)	20kp (P8/2) 10kp (P8/4)
			F			0.8±0.2				*	-
			A			0.55 max.				4kp (P8/4)	10kp (P8/4)
			B			0.95 max.				4kp (P8/4)	10kp (P8/4)
21	2012	0805	C	2.0±0.10	1.25±0.10	1.00 max.	0.20	0.75	0.70	4kp (E8/4)	10kp (E8/4)
			D			0.60±0.1				4kp (P8/4)	10kp (P8/4)
			E			0.85±0.10				4kp (P8/4)	10kp (P8/4)
			F			1.05±0.10				3kp (E8/4)	10kp (E8/4)
			G	2.0±0.15	1.25±0.15	1.25±0.10				3kp (E8/4)	10kp (E8/4)
			H			0.55 max.				4kp (P8/4)	10kp (P8/4)
			J			0.95 max.				4kp (P8/4)	10kp (P8/4)
			K			1.25±0.15				3kp (E8/4)	10kp (E8/4)
			L	2.0±0.20	1.25±0.20	0.95 max.				4kp (P8/4)	10kp (P8/4)
			M			1.25±0.20				3kp (E8/4)	10kp (E8/4)
			A			0.85±0.10				4kp (P8/4)	10kp (P8/4)
			B			0.95 max.				4kp (P8/4)	10kp (P8/4)
316	3216	1206	C	3.2±0.20	1.6±0.15	1.00 max.	0.30	0.85	1.40	4kp (E8/4)	10kp (E8/4)
			D			1.15±0.10				3kp (E8/4)	10kp (E8/4)
			E			1.25±0.10				3kp (E8/4)	10kp (E8/4)
			F			1.6±0.15				2.5kp (E8/4)	5kp (E8/4)
			G	3.2±0.20	1.6±0.20	0.95 max.				4kp (P8/4)	10kp (P8/4)
			H			1.00 max.				4kp (E8/4)	10kp (E8/4)
			J			1.6±0.20				2.5kp (E8/4)	5kp (E8/4)
			A			1.00 max.				4kp (E8/4)	10kp (E8/4)
32	3225	1210	B	3.2±0.20	2.5±0.20	1.40 max.	0.30	1.00	1.40	3kp (E8/4)	10kp (E8/4)
			C			1.60 max.				2.5kp (E8/4)	5kp (E8/4)
			D			1.6±0.15				2.5kp (E8/4)	5kp (E8/4)
			E			2.20 max.				2kp (E8/4)	5kp (E8/4)
			F	3.2±0.20	2.5±0.20	2.0±0.2				2kp (E8/4)	5kp (E8/4)
			G			2.5±0.2				1kp (E8/4)	4kp (E8/4)
			A			1.6 max.				2kp (E12/4)	-
			B			2.2 max.				2kp (E12/4)	-
42	4520	1808	A	4.5±0.20	2.0±0.20	2.0 max.	0.15	0.85	2.60	1kp (E12/8)	-
			B			2.0±0.2				1kp (E12/8)	-
			C			2.5 max.				0.5kp (E12/8)	-
			D			2.5±0.2				0.5kp (E12/8)	-
			E			2.8 max.				0.5kp (E12/8)	-
43	4532	1812	F			2.8±0.2	0.30	1.10	2.00	0.5kp (E12/8)	-
			A			2.2 max.				2kp (12/8)	-
			B			2.0 max.				1kp (E12/8)	-
			C			2.5 max.				0.5kp (E12/8)	-
			D			2.5±0.2				0.5kp (E12/8)	-
52	5720	2208	E			2.8 max.	0.30	1.40	2.50	0.5kp (E12/8)	-
			F			2.8±0.2				0.5kp (E12/8)	-
			A			2.2 max.				2kp (12/8)	-
			B			2.0 max.				1kp (E12/8)	-
			C			2.5 max.				0.5kp (E12/8)	-
55	5750	2220	D			2.8 max.				0.5kp (E12/8)	-
			A			2.2 max.				2kp (12/8)	-
			B			2.0 max.				1kp (E12/8)	-

Note: Taping denotes the quantity packaged per reel (kp means 1000 pieces).

\* Please contact us.

### KYOCERA PART NUMBER

CM 21 X7R 104 K 50 A T □ □ □

### SERIES CODE

CM = General Purpose      CL = ICs  
CT = Low Profile          CF = High Voltage  
CA = Arrays                DM = Automotive

### SIZE CODE

SIZE	EIA (JIS)	SIZE	EIA (JIS)	SIZE	EIA (JIS)
02	= 01005 (0402)	32	= 1210 (3225)	D11	= 0405 (1014)/ 2 cap
03	= 0201 (0603)	42	= 1808 (4520)	F12	= 0508 (1220)/ 4 cap
05	= 0402 (1005)	43	= 1812 (4532)		
105	= 0603 (1608)	52	= 2208 (5720)		
21	= 0805 (2012)	55	= 2220 (5750)		
316	= 1206 (3216)				

### DIELECTRIC CODE

#### CODE EIA CODE

CG = C0G (NPO)      X7S = X7S (Option)  
X5R = X5R              X6S = X6S (Option)  
X7R = X7R              Y5V = Y5V

Negative temperature coefficient dielectric types are available on request.

### CAPACITANCE CODE

Capacitance expressed in pF.

Two significant digits plus number of zeros.

For Values < 10pF, Letter R denotes decimal point,

eg. 100000pF = 104      1.5pF = 1R5  
0.1μF = 104      0.5pF = R50  
4700pF = 472      100μF = 107

### TOLERANCE CODE

A = ±0.05pF (option)      D = ±0.5pF      K = ±10%  
B = ±0.1pF                  G = ±2% (option)      M = ±20%  
C = ±0.25pF                J = ±5%                Z = -20 to +80%

### VOLTAGE CODE

04 = 4VDC	100 = 100VDC	1000 = 1000VDC
06 = 6.3VDC	250 = 250VDC	2000 = 2000VDC
10 = 10VDC	400 = 400VDC	3000 = 3000VDC
16 = 16VDC	630 = 630VDC	4000 = 4000VDC
25 = 25VDC		
35 = 35VDC		
50 = 50VDC		

### TERMINATION CODE

A = Nickel Barrier/ Tin      K = Nickel Barrier/ Au

### PACKAGING CODE

B = Bulk	H = 7" Reel Taping & 2mm Cavity pitch
C = Bulk Cassette (option)	N = 13" Reel Taping & 2mm Cavity pitch
T = 7" Reel Taping & 4mm or 8mm*1 Cavity pitch	W = 13" Reel Taping & 1mm Cavity pitch
Q = 7" Reel Taping & 1mm Cavity pitch	* P = 7" Reel Taping & 1mm Cavity pitch
L = 13" Reel Taping & 4mm Cavity pitch	* Carrier tape width 4mm.
	*1 Applied for size 43 to 55.

### OPTION

Thickness max. value is indicated in CT series

EX. 125 → 1.25mm max.  
095 → 0.95mm max.

### Temperature Compensation Type

Dielectric Value (pF)	C0G (NPO) 0 ppm/ °C	UΔ (N750) -750 ppm/ °C	SL +350 to -1000ppm/ °C
0.5 to 2.7	CK	UK	SL
3.0 to 3.9	CJ	UJ	SL
4.0 to 9.0	CH	UJ	SL
≥10	CG	UJ	SL

K = ±250ppm/ °C, J = ±120ppm/ °C, H = ±60ppm/ °C, G = ±30ppm/ °C  
e.g. CG = 0±30ppm/ °C

Note: All parts of C0G will be marked as "CG" but will conform to the above table.

### High Dielectric Constant Type

EIA Dielectric	Temperature Range	ΔC max.
X5R	-55 to 85°C	±15%
X7R	-55 to 125°C	
*X7S	-55 to 125°C	±22%
*X6S	-55 to 105°C	
Y5V	-30 to 85°C	-82 to +22%

\* option

### Available Tolerances

Dielectric materials, capacitance values and tolerances are available in the following combinations only:

EIA Dielectric	Tolerance	Capacitance
C0G	C=±0.25pF D=±0.50pF	*1 <10pF
	*3 A=±0.05pF B=±0.1pF	<0.5pF ≤5pF
	*3 G=±2% J=±5% K=±10%	≥10pF E12 Series
	*3 X6S X5R *3 X7S X7R	*2 K=±10% M=±20%
Y5V	Z=-20% to +80%	*4 E3 Series

Note:

\*1 Nominal values below 10pF are available in the standard values of 0.5pF, 1.0pF, 1.5pF, 2.0pF, 3.0pF, 4.0pF, 5.0pF, 6.0pF, 7.0pF, 8.0pF, 9.0pF

\*2 J = ±5% for X7R (X5R) is available on request.

\*3 option

\*4 E6 series is available on request.

### E Standard Number

E3	E6	E12	E24 (Option)	
1.0	1.0	1.0	1.0	1.1
		1.2	1.2	1.3
	1.5	1.5	1.5	1.6
		1.8	1.8	2.0
2.2	2.2	2.2	2.2	2.4
		2.7	2.7	3.0
	3.3	3.3	3.3	3.6
		3.9	3.9	4.3
4.7	4.7	4.7	4.7	5.1
		5.6	5.6	6.2
	6.8	6.8	6.8	7.5
		8.2	8.2	9.1

## Features

We offer a diverse product line ranging from ultra-compact (0.4×0.2mm) to large (4.5×3.2mm) components configured for a variety of temperature characteristics, rated voltages, and packages. We offer the choice and flexibility for almost any applications.

## Applications

This standard type is ideal for use in a wide range of applications, from commercial to industrial equipment.


## Temperature Compensation Dielectric

Size (EIA Code)	CM02 (01005)	CM03 (0201)					CM05 (0402)	CM105 (0603)	CM21 (0805)			
Temperature	CΔ*1	CΔ*1		UΔ*2		SL	CΔ*1	SL	CΔ*1	CΔ*1		
Rated Voltage (VDC)	16	25	50	16	25	25	50	50	50	16	25	50
Capacitance (pF)												
R20 0.2				B								
R50 0.5												
1R0 1.0												
1R5 1.5												
2.0												
3.0												
4.0												
5.0												
6.0												
7.0												
8.0												
9.0												
100 10	A	B	B		B	B						
120 12			B									
15 15												
18 18												
22 22												
27 27												
33 33												
39 39												
47 47												
56 56												
68 68												
82 82												
101 100												
121 120							D	D				
150 150												
180 180												
220 220												
270 270												
330 330												
390 390												
470 470												
560 560												
680 680									B			
820 820												
102 1000												
122 1200												E
1500 1500												
1800 1800												
2200 2200												
2700 2700												
3300 3300												
3900 3900												
4700 4700												
5600 5600												
6800 6800												
8200 8200												
103 10000										G		
123 12000												
15000 15000												
18000 18000												

<Standard Capacitance Value>

E12 Series

Please contact for capacitance value other than standard.

 Optional Spec.

\*1: CG,CH,CJ,CK

\*2: UJ,UK

Alphabets in capacitance chart denote dimensions.

Please refer to the below table for detail.

(Example)

In case of "B" for CM03;

L : 0.6±0.03mm

W : 0.3±0.03mm

T : 0.3±0.03mm

Size	Size Code	Dimension (mm)		
		L	W	T
02	A	0.4±0.02	0.2±0.02	0.2±0.02
03	B	0.6±0.03	0.3±0.03	0.3±0.03
05	D	1.0±0.05	0.5±0.05	0.5±0.05
105	B	1.6±0.10	0.8±0.10	0.8±0.10
21	E	2.0±0.10	1.25±0.10	0.85±0.10
	G			1.25±0.10

## X5R Dielectric

Size (EIA Code)	CM02 (01005)	CM03 (0201)	CM05 (0402)	CM105 (0603)	CM21 (0805)
Rated Voltage (VDC) Capacitance (pF)	6.3 10	6.3 10 16 25	4 6.3 10 16 25	4 6.3 10 16 25 50	4 6.3 10 16 25 50
101 100					
151 150					
220 220					
330 330					
470 470					
680 680					
102 1000					
152 1500					
2200 2200					
3300 3300					
4700 4700					
6800 6800					
103 10000					
153 15000					
22000 22000					
33000 33000					
47000 47000					
68000 68000					
104 100000					
220000 220000					
470000 470000					
105 1000000					
2200000 2200000					
4700000 4700000					
106 10000000					
22000000 22000000					
47000000 47000000					
107 100000000					


Size (EIA Code)	CM316 (1206)	CM32 (1210)	CM43 (1812)
Rated Voltage (VDC) Capacitance (pF)	6.3 10 16 25 50 100	4 6.3 10 16 25 50	6.3 50
105 220000			
470000 470000			
1000000 1000000			
2200000 2200000			
4700000 4700000			
106 10000000			
22000000 22000000			
47000000 47000000			
107 100000000			

&lt;Standard Capacitance Value&gt;

CM21 size and smaller : E6 Series

CM316 size and larger / capacitance value of 0.1μF and larger : E3 Series

Please contact for capacitance value other than standard.

 Optional Spec.

Two digits alphanumeric in capacitance chart denote dimensions and tan δ.  
Please refer to the below table for detail.

(Example)

In case of "B2" for CM03;

L : 0.6±0.03mm

W : 0.3±0.03mm

T : 0.3±0.03mm

Tan δ : 3.5% max.

Size	Size Code	Dimension (mm)		
		L	W	T
02	A	0.4±0.02	0.2±0.02	0.2±0.02
	B	0.6±0.03	0.3±0.03	0.3±0.03
03	C	0.6±0.05	0.3±0.05	0.3±0.05
	D	0.6±0.09	0.3±0.09	0.3±0.09
	D	1.0±0.05	0.5±0.05	0.5±0.05
	F	1.0±0.10	0.5±0.10	0.5±0.10
	G	1.0±0.15	0.5±0.15	0.5±0.15
105	B	1.6±0.10	0.8±0.10	0.8±0.10
	D	1.6±0.15	0.8±0.15	0.8±0.15
	G	2.0±0.10	1.25±0.10	1.25±0.10
21	K	2.0±0.15	1.25±0.15	1.25±0.15
	M	2.0±0.20	1.25±0.20	1.25±0.20

Size	Size Code	Dimension (mm)		
		L	W	T
	D	3.2±0.20	1.6±0.15	1.15±0.10
316	F	3.2±0.20	1.6±0.15	1.6±0.15
	J	3.2±0.20	1.6±0.20	1.6±0.20
	B	3.2±0.20	2.5±0.20	1.40 max.
	C	3.2±0.20	2.5±0.20	1.60 max.
32	F	3.2±0.20	2.5±0.20	2.0±0.2
	G	3.2±0.20	2.5±0.20	2.5±0.2
	D	4.5±0.30	3.2±0.20	2.5±0.2
43	F	4.5±0.30	3.2±0.20	2.8±0.2

Tan δ Code	Tan δ
1	2.5% max.
2	3.5% max.
3	5.0% max.
4	7.0% max.
5	7.5% max.
7	10.0% max.
8	12.5% max.
9	20.0% max.

## X7R Dielectric

Size (EIA Code)	CM02 (01005)	CM03 (0201)			CM05 (0402)		CM105 (0603)					CM21 (0805)				
Rated Voltage (VDC) Capacitance (pF)	10	10	16	25	16	25	6.3	10	16	25	50	6.3	10	16	25	50
101 100	<div>A8</div>															
151 150																
220																
330																
470	<div>A8</div>															
680																
102 1000																
152 1500																
2200																
3300																
4700																
6800																
103 10000																
153 15000																
22000																
33000																
47000																
68000																
104 100000																
220000																
470000																
680000																
105 1000000																
2200000																
4700000																
106 10000000																
22000000																

Size (EIA Code)	CM316 (1206)						CM32 (1210)					CM43 (1812)	
Rated Voltage (VDC) Capacitance (pF)	6.3	10	16	25	50	100	10	16	25	50	100	50	100
104 47000													
100000													
220000													
470000													
105 1000000													
2200000													
4700000													
106 10000000													
22000000													

Optional Spec.

<Standard Capacitance Value>

CM21 size and smaller : E6 Series

CM316 size and larger / capacitance value of 0.1μF and larger : E3 Series

Please contact for capacitance value other than standard.

Two digits alphanumeric in capacitance chart denote dimensions and tan δ.  
Please refer to the below table for detail.

(Example)

In case of "B3" for CM03;

L : 0.6±0.03mm

W : 0.3±0.03mm

T : 0.3±0.03mm

Tan δ : 5.0% max.

Size	Size Code	Dimension (mm)		
		L	W	T
02	A	0.4±0.02	0.2±0.02	0.2±0.02
03	B	0.6±0.03	0.3±0.03	0.3±0.03
05	D	1.0±0.05	0.5±0.05	0.5±0.05
105	B	1.6±0.10	0.8±0.10	0.8±0.10
	D	1.6±0.15	0.8±0.15	0.8±0.15
21	G	2.0±0.10	1.25±0.10	1.25±0.10
	M	2.0±0.20	1.25±0.20	1.25±0.20
316	A			0.85±0.10
	D	3.2±0.20	1.6±0.15	1.15±0.10
	F			1.6±0.15
	J	3.2±0.20	1.6±0.20	1.6±0.20
32	B			1.40 max.
	F	3.2±0.20	2.5±0.20	2.0±0.2
	G			2.5±0.2
43	B	4.5±0.30	3.2±0.20	2.0±0.2
	D			2.5±0.2

Tan δ Code	Tan δ
1	2.5% max.
2	3.5% max.
3	5.0% max.
5	7.5% max.
8	12.5% max.

## Y5V Dielectric

Size (EIA Code)	CM05 (0402)	CM105 (0603)		CM21 (0805)			CM316 (1206)			CM32 (1210)		
Rated Voltage (VDC) Capacitance (pF)	10	10	16	10	16	25	10	16	25	10	16	25
102 1000 472 2200 473 4700												
103 10000 473 22000 474 47000												
104 100000 474 220000 475 470000	<b>D8</b>		<b>B6</b>									
105 1000000 475 2200000 476 4700000		<b>B8</b>		<b>G8</b>	<b>G6</b>	<b>G4</b>		<b>D6</b>	<b>D4</b>			
106 10000000 476 22000000 477 47000000				<b>G9</b>			<b>F8</b> <b>F9</b>	<b>F6</b>		<b>F8</b>	<b>C6</b>	<b>C6</b>

<Standard Capacitance Value>

E3 Series

Please contact for capacitance value other than standard.

Two digits alphanumeric in capacitance chart denote dimensions and tan  $\delta$ .  
Please refer to the below table for detail.

(Example)

In case of "C8" for CM05;  
L : 1.0±0.05mm  
W : 0.5±0.05mm  
T : 0.5±0.05mm  
Tan  $\delta$  : 12.5% max.

Size	Size Code	Dimension (mm)		
		L	W	T
<b>05</b>	<b>D</b>	1.0±0.05	0.5±0.05	0.5±0.05
<b>105</b>	<b>B</b>	1.6±0.10	0.8±0.10	0.8±0.10
<b>21</b>	<b>G</b>	2.0±0.10	1.25±0.10	1.25±0.10
<b>316</b>	<b>D</b>	3.2±0.20	1.6±0.15	1.15±0.10
	<b>F</b>	3.2±0.20	1.6±0.15	1.6±0.15
<b>32</b>	<b>C</b>	3.2±0.20	2.5±0.20	1.60 max.
	<b>F</b>	3.2±0.20	2.5±0.20	2.0±0.2

Tan $\delta$ Code	Tan $\delta$
<b>3</b>	5.0% max.
<b>4</b>	7.0% max.
<b>6</b>	9.0% max.
<b>8</b>	12.5% max.
<b>9</b>	16.0% max.



### Test Conditions and Specifications for Temperature Compensation Type (CΔ to UΔ • SL Characteristics) CM/ CT/ CF Series

Test Items		Test Conditions	Specifications									
Capacitance Value (C)		<table><tr><th>Capacitance</th><th>Frequency</th><th>Volt</th></tr><tr><td>C≤1000pF</td><td>1MHz±10%</td><td rowspan="2">0.5 to 5Vrms</td></tr><tr><td>C&gt;1000pF</td><td>1kHz±10%</td></tr></table>	Capacitance	Frequency	Volt	C≤1000pF	1MHz±10%	0.5 to 5Vrms	C>1000pF	1kHz±10%	Within tolerance	
Capacitance	Frequency	Volt										
C≤1000pF	1MHz±10%	0.5 to 5Vrms										
C>1000pF	1kHz±10%											
Q			C≥30pF : Q≥1000 C<30pF : Q≥400+20C									
Insulation Resistance (IR)		Measured after the rated voltage is applied for 1 minute at room ambient. For the rated voltage of over 630V, apply 500V for 1 minute at room ambient. The charge and discharge current of the capacitor must not exceed 50mA.	Over 10000MΩ or 500MΩ • μF, whichever is less									
Dielectric Resistance		Apply 3 times of the rated voltage for 1 to 5 seconds. Apply 1.5 times when the rated voltage is 250V or over. Apply 1.2 times when the rated voltage is 630V or over. The charge and discharge current of the capacitor must not exceed 50mA.	No problem observed									
Appearance		Microscope	No problem observed									
Termination Strength		Apply a sideward force of 500g (5N) to a PCB-mounted sample. Apply 2N for 0201, and 1N for 01005 size.	No problem observed									
Bending Strength		Glass epoxy PCB: Fulcrum spacing: 90mm, duration time 10 seconds.	No significant damage at 1mm bent									
Vibration Test	Appearance	Vibration frequency: 10 to 55 (Hz)	No problem observed									
	ΔC	Amplitude: 1.5mm Sweeping condition: 10→55→10Hz/ 1 minute in X, Y and Z	Within Tolerance									
	Q	Directions: 2 hours each, 6 hours total.	C≥30pF : Q≥1000 C<30pF : Q≥400+20C									
Soldering Heat Resistance	Appearance	Soak the sample in 260°C±5°C solder for 10±0.5 seconds and place in room ambient, and measure after 24±2 hours.	No problem observed									
	ΔC	(Pre-heating conditions)	Within ±2.5% or ±0.25pF, whichever is larger									
	Q	<table><tr><th>Order</th><th>Temperature</th><th>Time</th></tr><tr><td>1</td><td>80 to 100°C</td><td>2 minutes</td></tr><tr><td>2</td><td>150 to 200°C</td><td>2 minutes</td></tr></table>	Order	Temperature	Time	1	80 to 100°C	2 minutes	2	150 to 200°C	2 minutes	C≥30pF : Q≥1000 C<30pF : Q≥400+20C
	Order	Temperature	Time									
	1	80 to 100°C	2 minutes									
2	150 to 200°C	2 minutes										
IR		Over 10000MΩ or 500MΩ • μF whichever is less										
Withstanding Voltage	The charge and discharge current of the capacitor must not exceed 50mA for IR and withstanding voltage measurement.	Resist without problem										
Solderability		Soaking condition <table><tr><td>Sn-3Ag-0.5Cu</td><td>245±5°C</td><td>3±0.5 sec.</td></tr><tr><td>Sn63 Solder</td><td>235±5°C</td><td>2±0.5 sec.</td></tr></table>	Sn-3Ag-0.5Cu	245±5°C	3±0.5 sec.	Sn63 Solder	235±5°C	2±0.5 sec.	Solder coverage : 90% min.			
Sn-3Ag-0.5Cu	245±5°C	3±0.5 sec.										
Sn63 Solder	235±5°C	2±0.5 sec.										
Temperature Cycle	Appearance	(Cycle)	No problem observed									
	ΔC	Room temperature (3min.)→	Within ±2.5% or ±0.25pF, whichever is larger									
	Q	Lowest operation temperature (30min.)→ Room temperature (3min.)→	C≥30pF : Q≥1000 C<30pF : Q≥400+20C									
	IR	Highest operation temperature(30min.)	Over 10000MΩ or 500MΩ • μF, whichever is less									
	Withstanding Voltage	After 5 cycles, measure after 24±2 hours.  The charge and discharge current of the capacitor must not exceed 50mA for IR and withstanding voltage measurement.	Resist without problem									
Load Humidity Test (Except CF Series)	Appearance	After applying rated voltage for 500+12/-0 hours in pre-condition at 40°C±2°C, humidity 90 to 95%RH, allow parts to stabilize for 24±2 hours, at room temperature before measurement.	No problem observed									
	ΔC	The charge and discharge current of the capacitor must not exceed 50mA for IR measurement.	Within ±7.5% or ±0.75pF, whichever is larger									
	Q		C≥30pF : Q≥200 C<30pF : Q≥100+10C/ 3									
	IR		Over 500MΩ or 25MΩ • μF, whichever is less									
High-Temperature with Loading	Appearance	After applying twice the rated voltage at the temperature of 125±3°C for 1000+12/-0 hours, measure the sample after 24±2 hours.	No problem observed.									
	ΔC	Apply 1.5 times when the rated voltage is 250V or over. Apply 1.2 times when the rated voltage is 630V or over.	Within ±3% or ±0.3pF, whichever is larger									
	Q	The charge and discharge current of the capacitor must not exceed 50mA for IR measurement.	C≥30pF : Q≥350 10pF<C<30pF : Q≥275+5C/ 2 C<10pF : Q≥200+10C									
	IR		Over 1000MΩ or 50MΩ • μF, whichever is less									

Please ask for individual specification for the hatched range in previous chart.

### Test Conditions and Specifications for High Dielectric Type (X5R, X7R) CM/ CT/ CA Series

Test Items		Test Conditions	Specifications									
Capacitance Value (C)		Measure after heat treatment	Within tolerance									
Tanδ (%)		<table><tr><th>Capacitance</th><th>Frequency</th><th>Volt</th></tr><tr><td>C≤10μF</td><td>1kHz±10%</td><td>1.0±0.2Vrms</td></tr><tr><td>C&gt;10μF</td><td>120Hz±10%</td><td>0.5±0.2Vrms</td></tr></table>	Capacitance	Frequency	Volt	C≤10μF	1kHz±10%	1.0±0.2Vrms	C>10μF	120Hz±10%	0.5±0.2Vrms	Refer to capacitance chart
	Capacitance	Frequency	Volt									
	C≤10μF	1kHz±10%	1.0±0.2Vrms									
C>10μF	120Hz±10%	0.5±0.2Vrms										
Insulation Resistance (IR)		Measured after the rated voltage is applied for 1 minute at room ambient. The charge and discharge current of the capacitor must not exceed 50mA.	Over 10000MΩ or 500MΩ • μF, whichever is less									
Dielectric Resistance		Apply 2.5 times of the rated voltage for 1 to 5 seconds. The charge and discharge current of the capacitor must not exceed 50mA.	No problem observed									
Appearance		Microscope	No problem observed									
Termination Strength		Apply a sideward force of 500g (5N) to a PCB-mounted sample. note : 2N for 0201 size in for 01005 size. Exclude CT series with thickness of less than 0.66mm.	No problem observed									
Bending Strength		Glass epoxy PCB: Fulcrum spacing: 90mm, duration time 10 seconds. Exclude CT series with thickness of less than 0.66mm.	No significant damage at 1mm bent									
Vibration Test	Appearance	Take the initial value after heat treatment.	No problem observed									
	ΔC	Vibration frequency: 10 to 55 (Hz) Amplitude: 1.5mm	Within tolerance									
	Tanδ (%)	Sweeping condition: 10→55→10Hz/ 1 minute in X, Y and Z Directions: 2 hours each, 6 hours total.	Within tolerance									
Soldering Heat Resistance	Appearance	Take the initial value after heat treatment.	No problem observed									
	ΔC	Soak the sample in 260°C±5°C solder for 10±0.5 seconds and place in room ambient, and measure after 24±2 hours.	Within ±7.5%									
	Tanδ (%)	(Pre-heating conditions)	Within tolerance									
	IR		Over 10000MΩ or 500MΩ • μF, whichever is less									
	Withstanding Voltage	<table><tr><th>Order</th><th>Temperature</th><th>Time</th></tr><tr><td>1</td><td>80 to 100°C</td><td>2 minutes</td></tr><tr><td>2</td><td>150 to 200°C</td><td>2 minutes</td></tr></table> The charge and discharge current of the capacitor must not exceed 50mA for IR and withstanding voltage measurement.	Order	Temperature	Time	1	80 to 100°C	2 minutes	2	150 to 200°C	2 minutes	Resist without problem
Order	Temperature	Time										
1	80 to 100°C	2 minutes										
2	150 to 200°C	2 minutes										
Solderability		Soaking condition <table><tr><td>Sn-3Ag-0.5Cu</td><td>245±5°C</td><td>3±0.5 sec.</td></tr><tr><td>Sn63 Solder</td><td>235±5°C</td><td>2±0.5 sec.</td></tr></table>	Sn-3Ag-0.5Cu	245±5°C	3±0.5 sec.	Sn63 Solder	235±5°C	2±0.5 sec.	Solder coverage : 90% min.			
Sn-3Ag-0.5Cu	245±5°C	3±0.5 sec.										
Sn63 Solder	235±5°C	2±0.5 sec.										
Temperature Cycle	Appearance	Take the initial value after heat treatment.	No problem observed									
	ΔC	(Cycle)	Within ±7.5%									
	Tanδ (%)	Room temperature (3min.)→ Lowest operation temperature (30min.)→ Room temperature (3min.)→	Within tolerance									
	IR	Highest operation temperature(30min.) After 5 cycles, measure after 24±2 hours. The charge and discharge current of the capacitor must not exceed 50mA for IR and withstanding voltage measurement.	Over 10000MΩ or 500MΩ • μF, whichever is less									
	Withstanding Voltage		Resist without problem									
Load Humidity Test	Appearance	Take the initial value after voltage treatment.	No problem observed									
	ΔC	After applying rated voltage for 500+12/-0 hours in pre-condition at 40°C±2°C, humidity 90 to 95%RH, allow parts to stabilize for 24±2 hours, at room temperature before measurement.	Within ±12.5%									
	Tanδ (%)	The charge and discharge current of the capacitor must not exceed 50mA for IR measurement.	200% max. of initial value									
	IR		Over 500MΩ or 25MΩ • μF, whichever is less									
High-Temperature with Loading	Appearance	Take the initial value after voltage treatment.	No problem observed									
	ΔC	After applying twice the rated voltage at the highest operation temperature for 1000+12/-0 hours, measure the sample after 24±2 hours.	Within ±12.5%									
	Tanδ (%)	The charge and discharge current of the capacitor must not exceed 50mA for IR measurement.	200% max. of initial value									
	IR	Apply 1.5 times when the rated voltage is 10V or less. Applied voltages for respective products are indicated in the below chart.	Over 1000MΩ or 50MΩ • μF, whichever is less									

Pre-treatment	Heat	Keep specimen at 150+0/-10°C for 1 hour, leave specimen at room ambient for 24±2 hours.
	Voltage	Apply the same test condition for 1 hour, then leave the specimen at room ambient for 24±2 hours.

High-temperature with Loading Applied Voltage (Rated Voltage × □ )

Applied Voltage	Rated Voltage	Products
×1.3	4V	CT03X5R104
	6.3V	CM105X5R475, CM316X5R476 CT05X5R104, CT21X5R106, CT03X5R104
	16V	CM105X7R474-105, CM21X7R105-475, CM316X7R475-106, CM32X7R106-226, CM05X5R224, CM105X5R225, CM21X5R475-106, CM316X5R226 CT105X5R105, CT21X5R225-475, CT316X5R106, CM03X5R332-103
×1.5	25V	CM105X7R474, CM21X7R105-225, CM316X7R475, CM32X7R106, CM105X5R474-105, CM21X5R225-106, CM316X5R106, CM32X5R106-226 CT316X5R225-106, CM03X5R152-103
	50V	CM21X5R105, CM32X5R106, CM32X7R106 CT21X5R225, CT316X5R105-475
	100V	CM32X7RK74, CM43X7R105

Please ask for individual specification for the hatched range in previous chart.

### Test Conditions and Specifications for High Dielectric Type (Y5V) CM/ CT/ CA Series

Test Items		Test Conditions		Specifications									
Capacitance Value (C)		Measure after heat treatment		Within tolerance									
Tanδ (%)		<table><tr><th>Frequency</th><th>Volt</th></tr><tr><td>1kHz±10%</td><td>1.0±0.2Vrms</td></tr></table>	Frequency	Volt	1kHz±10%	1.0±0.2Vrms		Refer to capacitance chart					
Frequency	Volt												
1kHz±10%	1.0±0.2Vrms												
Insulation Resistance (IR)		Measured after the rated voltage is applied for 1 minute at room ambient.		Over 10000MΩ or 500MΩ • μF, whichever is less									
Dielectric Resistance		Apply 2.5 times of the rated voltage for 1 to 5 seconds. The charge and discharge current of the capacitor must not exceed 50mA.		No problem observed									
Appearance		Microscope		No problem observed									
Termination Strength		Apply a sideward force of 500g (5N) to a PCB-mounted sample. Exclude CT series with thickness of less than 0.66mm.		No problem observed									
Bending Strength		Glass epoxy PCB: Fulcrum spacing: 90mm, duration time 10 seconds. Exclude CT series with thickness of less than 0.66mm.		No significant damage at 1mm bent									
Vibration Test	Appearance	Take the initial value after heat treatment.		No problem observed									
	ΔC	Vibration frequency: 10 to 55 (Hz) Amplitude: 1.5mm		Within tolerance									
	Tanδ (%)	Sweeping condition: 10→55→10Hz/ 1 minute in X, Y and Z Directions: 2 hours each, 6 hours total.		Within tolerance									
Soldering Heat Resistance	Appearance	Take the initial value after heat treatment.		No problem observed									
	ΔC	Soak the sample in 260°C±5°C solder for 10±0.5 seconds and place in room ambient, and measure after 24±2 hours.		Within ±20%									
	Tanδ (%)	(Pre-heating conditions)		Within tolerance									
	IR	<table><tr><th>Order</th><th>Temperature</th><th>Time</th></tr><tr><td>1</td><td>80 to 100°C</td><td>2 minutes</td></tr><tr><td>2</td><td>150 to 200°C</td><td>2 minutes</td></tr></table>		Order	Temperature	Time	1	80 to 100°C	2 minutes	2	150 to 200°C	2 minutes	Over 10000MΩ or 500MΩ • μF, whichever is less
	Order	Temperature	Time										
1	80 to 100°C	2 minutes											
2	150 to 200°C	2 minutes											
Withstanding Voltage	The charge and discharge current of the capacitor must not exceed 50mA for IR and withstanding voltage measurement.		Resist without problem										
Solderability		Soaking condition <table><tr><td>Sn-3Ag-0.5Cu</td><td>245±5°C</td><td>3±0.5 sec.</td></tr><tr><td>Sn63 Solder</td><td>235±5°C</td><td>2±0.5 sec.</td></tr></table>		Sn-3Ag-0.5Cu	245±5°C	3±0.5 sec.	Sn63 Solder	235±5°C	2±0.5 sec.	Solder coverage : 90% min.			
Sn-3Ag-0.5Cu	245±5°C	3±0.5 sec.											
Sn63 Solder	235±5°C	2±0.5 sec.											
Temperature Cycle	Appearance	Take the initial value after heat treatment.		No problem observed									
	ΔC	(Cycle) Room temperature (3min.)→		Within ±20%									
	Tanδ (%)	Lowest operation temperature (30min.)→ Room temperature (3min.)→		Within tolerance									
	IR	Highest operation temperature(30min.) After 5 cycles, measure after 24±2 hours.		Over 10000MΩ or 500MΩ • μF, whichever is less									
	Withstanding Voltage	The charge and discharge current of the capacitor must not exceed 50mA for IR and withstanding voltage measurement.		Resist without problem									
Load Humidity Test	Appearance	Take the initial value after voltage treatment.		No problem observed									
	ΔC	After applying rated voltage for 500+12/ -0 hours in pre-condition at 40°C±2°C, humidity 90 to 95%RH, allow parts to stabilize for 24±2 hours, at room temperature before measurement.		Within ±30%									
	Tanδ (%)	The charge and discharge current of the capacitor must not exceed 50mA for IR measurement.		150% max. of initial value									
	IR			Over 500MΩ or 25MΩ • μF, whichever is less									
High-Temperature with Loading	Appearance	Take the initial value after voltage treatment.		No problem observed									
	ΔC	After applying twice the rated voltage at the highest operation temperature for 1000+12/ -0 hours, measure the sample after 24±2 hours.		Within ±30%									
	Tanδ (%)	The charge and discharge current of the capacitor must not exceed 50mA for IR measurement.		150% max. of initial value									
	IR			Over 1000MΩ or 50MΩ • μF, whichever is less									
Pre-treatment	Heat	Keep specimen at 150+0/ -10°C for 1 hour, leave specimen at room ambient for 24±2 hours.											
	Voltage	Applv the same test condition for 1 hour, then leave the specimen at room ambient for 24±2 hours.											


### Test Conditions and Specifications for High Dielectric Type (X7R) CF Series

Test Items		Test Conditions	Specifications									
Capacitance Value (C)		Measure after heat treatment	Within tolerance									
Tanδ (%)		<table><tr><th>Capacitance</th><th>Frequency</th><th>Volt</th></tr><tr><td>C≤10μF</td><td>1kHz±10%</td><td>1.0±0.2Vrms</td></tr></table>	Capacitance	Frequency	Volt	C≤10μF	1kHz±10%	1.0±0.2Vrms	Within ±2.5%			
Capacitance	Frequency	Volt										
C≤10μF	1kHz±10%	1.0±0.2Vrms										
Insulation Resistance (IR)		Measured after the rated voltage is applied for 1 minute at room ambient. Measured after the 500V is applied for 1 minute at room ambient for the rated voltage over 630V. The charge and discharge current of the capacitor must not exceed 50mA.	Over 10000MΩ or 500MΩ • μF, whichever is less Over 100MΩ • μF for CF316X7R104/ 250V and CF43X7R474/ 250V CF55X7R105/ 250V and CF55X7R224/ 630V									
Dielectric Resistance		Apply 1.5 times when the rated voltage is 250V or over, apply 1.2 times when the rated voltage is 630V or over for 1 to 5 seconds. The charge and discharge current of the capacitor must not exceed 50mA.	No problem observed									
Appearance		Microscope	No problem observed									
Termination Strength		Apply a sideward force of 500g (5N) to a PCB-mounted sample.	No problem observed									
Bending Strength		Glass epoxy PCB: Fulcrum spacing: 90mm, duration time 10 seconds.	No significant damage at 1mm bent									
Vibration Test	Appearance	Take the initial value after heat treatment. Vibration frequency: 10 to 55 (Hz) Amplitude: 1.5mm Sweeping condition: 10→55→10Hz/ 1 minute in X, Y and Z Directions: 2 hours each, 6 hours total.	No problem observed									
	ΔC		Within tolerance									
	Tanδ (%)		Within tolerance									
Soldering Heat Resistance	Appearance	Take the initial value after heat treatment. Soak the sample in 260°C±5°C solder for 10±0.5 seconds and place in room ambient, and measure after 24±2 hours. (Pre-heating conditions) <table><tr><th>Order</th><th>Temperature</th><th>Time</th></tr><tr><td>1</td><td>80 to 100°C</td><td>2 minutes</td></tr><tr><td>2</td><td>150 to 200°C</td><td>2 minutes</td></tr></table> The charge and discharge current of the capacitor must not exceed 50mA for IR and withstanding voltage measurement.	Order	Temperature	Time	1	80 to 100°C	2 minutes	2	150 to 200°C	2 minutes	No problem observed
	Order		Temperature	Time								
	1		80 to 100°C	2 minutes								
	2		150 to 200°C	2 minutes								
	ΔC		Within ±7.5%									
Tanδ (%)	Within tolerance											
IR	Over 10000MΩ or 500MΩ • μF, whichever is less Over 100MΩ • μF for CF316X7R104/ 250V and CF43X7R474/ 250V CF55X7R105/ 250V and CF55X7R224/ 630V											
Withstanding Voltage	Resist without problem											
Solderability		Soaking condition <table><tr><th>Sn-3Ag-0.5Cu</th><th>245±5°C</th><th>3±0.5 sec.</th></tr><tr><th>Sn63 Solder</th><th>235±5°C</th><th>2±0.5 sec.</th></tr></table>	Sn-3Ag-0.5Cu	245±5°C	3±0.5 sec.	Sn63 Solder	235±5°C	2±0.5 sec.	Solder coverage : 90% min.			
Sn-3Ag-0.5Cu	245±5°C	3±0.5 sec.										
Sn63 Solder	235±5°C	2±0.5 sec.										
Temperature Cycle	Appearance	Take the initial value after heat treatment. (Cycle) Room temperature (3min.)→ Lowest operation temperature (30min.)→ Room temperature (3min.)→ Highest operation temperature(30min.) After 5 cycles, measure after 24±2 hours. The charge and discharge current of the capacitor must not exceed 50mA for IR and withstanding voltage measurement.	No problem observed									
	ΔC		Within ±7.5%									
	Tanδ (%)		Within tolerance									
	IR		Over 10000MΩ or 500MΩ • μF, whichever is less Over 100MΩ • μF for CF316X7R104/ 250V and CF43X7R474/ 250V CF55X7R105/ 250V and CF55X7R224/ 630V									
	Withstanding Voltage		Resist without problem									
High-Temperature with Loading	Appearance	Take the initial value after voltage treatment. After applying specified voltage at the highest operation temperature for 1000+12/ -0 hours, then measure the sample after 24±2 hours. The applied voltage shall be; 1.5 times the rated voltage when the rated voltage is 250V or over. 1.2 times when the rated voltage is 630V or over. The charge and discharge current of the capacitor must not exceed 50mA for IR measurement.	No problem observed									
	ΔC		Within ±12.5%									
	Tanδ (%)		200% max. of initial value									
	IR		Over 1000MΩ or 50MΩ • μF, whichever is less									
Pre-treatment	Heat	Keep specimen at 150+0/ -10°C for 1 hour, leave specimen at room ambient for 24±2 hours.										
	Voltage	Apply the same test condition for 1 hour, then leave the specimen at room ambient for 24±2 hours.										



(Unit: mm)


Substrate for Electrical Tests



Size (EIA Code)	a	b	c
02 (01005)	0.15	0.50	0.20
03 (0201)	0.26	0.92	0.32
05 (0402)	0.4	1.4	0.5
105 (0603)	1.0	3.0	1.2
21 (0805)	1.2	4.0	1.65
316 (1206)	2.2	5.0	2.0
32 (1210)	2.2	5.0	2.9
42 (1808)	3.5	7.0	3.7
43 (1812)	3.5	7.0	3.7
52 (2208)	4.5	8.0	5.6
55 (2220)	4.5	8.0	5.6


Substrate for Bending Test

(Unit: mm)




\* 02, 03, 05 and array: 0.8±0.1mm

Substrate for Adhesion Strength Test




## Tape and Reel


### • Reel




F=1mm (02 Type)




F=1mm (02, 03, 05 Type)




F=2mm (03, 05, 105 Type)



F=4mm (105, D11, F12, 21, 316, 32, 42, 52 Type)



F=8mm (43, 55 Type)



## Reel

(Unit: mm)

Code Reel	A	B	C	D
7-inch Reel (CODE: T, H, Q)	180 <sup>+0</sup> <sub>-2.0</sub>	φ60 min.	13±0.5	21±0.8
7-inch Reel (CODE: P)	178±2.0			
13-inch Reel (CODE: L, N, W)	330±2.0			
Code Reel	E	W <sub>1</sub>	W <sub>2</sub>	R
7-inch Reel (CODE: T, H, Q)	2.0±0.5	10.5±1.5	16.5 max.	1.0
7-inch Reel (CODE: P)		4.35±0.3	6.95±1.0	
13-inch Reel (CODE: L, N, W)		9.5±1.0	16.5 max.	

\* Carrier tape width 8mm.

For size 42 (1808) or over, Tape width 12mm and W<sub>1</sub>: 14±1.5, W<sub>2</sub>: 18.4mm max.

## Carrier Tape


(Unit: mm)

Size (EIA Code)	A	B	F
02 (01005)*	0.23±0.02	0.43±0.02	1.0±0.02
	0.25±0.03	0.45±0.03	2.0±0.05
03 (0201)*	0.37±0.03	0.67±0.03	1.0±0.05
			2.0±0.05
05 (0402)*	0.65±0.1	1.15±0.1	1.0±0.05
			2.0±0.05
105 (0603)	1.0±0.2	1.8±0.2	4.0±0.1
21 (0805)	1.5±0.2	2.3±0.2	4.0±0.1
316 (1206)	2.0±0.2	3.6±0.2	4.0±0.1
32 (1210)	2.9±0.2	3.6±0.2	4.0±0.1
42 (1808)	2.4±0.2	4.9±0.2	4.0±0.1
43 (1812)	3.6±0.2	4.9±0.2	8.0±0.1
52 (2208)	2.4±0.2	6.0±0.2	4.0±0.1
55 (2220)	5.3±0.2	6.0±0.2	8.0±0.1
D11 (0405)	1.15±0.2	1.55±0.2	4.0±0.1
F12 (0508)	1.5±0.2	2.3±0.2	4.0±0.1


\* Option

(Unit: mm)

F	Carrier Tape	C	D	E	G	H	J
1.0 ±0.02	4mm Plastic	4.0 +0.08	1.8 ±0.02	0.9 ±0.05	—	2.0 ±0.04	0.8 ±0.04
1.0 ±0.05	1mm Paper	8.0 +0.3/-0.1	3.5 ±0.05	1.75 ±0.1	2.0 ±0.05	4.0 ±0.05	1.5 +0.1/-0
2.0 ±0.05	8mm Paper	8.0 ±0.3				4.0 ±0.1	
4.0 ±0.1	8mm Plastic						
8.0 ±0.1	12mm Plastic	12.0 ±0.3					




Detail of leader and trailer




Adhesive tape

- 1) The exfoliative strength when peeling off the top tape from the carrier tape by the method of the following figure shall be \*0.1 to 0.7N. \*02 Size: 0.1 to 0.5N
- 2) When the top tape is peeled off, the adhesive stays on the top tape.
- 3) Chip capacitors will be in a state free without being stuck on the thermal adhesive tape.



Bulk Case (Unit: mm)




• Please contact Kyocera for details.



### Dimensions for recommended typical land

Since the amount of solder (size of fillet) to be used has direct influence on the capacitor after mounting, the sufficient consideration is necessary.

When the amounts of solder is too much, the stress that a capacitor receives becomes larger. It may become the cause of a crack in the capacitor. When the land design of printed wiring board is considered, it is necessary to set up the form and size of land pattern so that the amount of solder is suitable.



### Design of printed circuit and Soldering

The recommended fillet height shall be 1/2 of the thickness of capacitors or 0.5mm. When mounting two or more capacitors in the common land, it is necessary to separate the land with the solder resist strike so that it may become the exclusive land of each capacitor.

### General, High-Voltage

(Unit: mm)

Size (EIA Code)	L×W	a	b	c
02 (01005)	0.4×0.2	0.13 to 0.20	0.12 to 0.18	0.20 to 0.23
03 (0201)	0.6×0.3	0.20 to 0.30	0.25 to 0.35	0.30 to 0.40
05 (0402)	1.0×0.5	0.30 to 0.50	0.35 to 0.45	0.40 to 0.60
105 (0603)	1.6×0.8	0.70 to 1.00	0.80 to 1.00	0.60 to 0.80
21 (0805)	2.0×1.25	1.00 to 1.30	1.00 to 1.20	0.80 to 1.10
316 (1206)	3.2×1.6	2.10 to 2.50	1.10 to 1.30	1.00 to 1.30
32 (1210)	3.2×2.5	2.10 to 2.50	1.10 to 1.30	1.90 to 2.30
42 (1808)	4.5×2.0	2.50 to 3.20	1.80 to 2.30	1.50 to 1.80
43 (1812)	4.5×3.2	2.50 to 3.20	1.80 to 2.30	2.60 to 3.00
52 (2208)	5.7×2.0	4.20 to 4.70	2.00 to 2.50	1.50 to 1.80
55 (2220)	5.7×5.0	4.20 to 4.70	2.00 to 2.50	4.20 to 4.70

### Automotive

(Unit: mm)

Size (EIA Code)	L×W	a	b	c
105 (0603)	1.6×0.8	0.60 to 0.90	0.80 to 1.00	0.70 to 1.00
21 (0805)	2.0×1.25	0.90 to 1.20	0.80 to 1.20	0.90 to 1.40
316 (1206)	3.2×1.6	1.40 to 1.90	1.00 to 1.30	1.30 to 1.80

### Arrays

(Unit: mm)


	a	b	c	d
F12 (0508)	0.5	0.5	0.3	0.5
D11 (0405)	0.69	0.28	0.3	0.64

### IC

(Unit: mm)

Size (EIA Code)	L×W	a	b	c
05 (0402)	0.5×1.0	0.15 to 0.20	0.20 to 0.30	0.90 to 1.20
105 (0603)	0.8×1.6	0.20 to 0.30	0.30 to 0.50	1.40 to 1.60

### Ideal Solder Height



Item	Not recommended example	Recommended example/ Separated by solder
Multiple parts mount		
Mount with leaded parts		
Wire soldering after mounting		
Overview		



### Mounting Design


The chip could crack if the PCB warps during processing after the chip has been soldered.

### Recommended chip position on PCB to minimize stress from PCB warpage



### Actual Mounting

- 1) If the position of the vacuum nozzle is too low, a large force may be applied to the chip capacitor during mounting, resulting in cracking.
- 2) During mounting, set the nozzle pressure to a static load of 100 to 300 gf.
- 3) To minimize the shock of the vacuum nozzle, provide a support pin on the back of the PCB to minimize PCB flexure.



- 4) Bottom position of pick up nozzle should be adjusted to the top surface of a substrate which camber is corrected.
- 5) To reduce the possibility of chipping and cracks, minimize vibration to chips stored in a bulk case.
- 6) The discharge pressure must be adjusted to the part size. Verify the pressure during setup to avoid fracturing or cracking the chips capacitors.

### Resin Mold

- 1) If a large amount of resin is used for molding the chip, cracks may occur due to contraction stress during curing. To avoid such cracks, use a low shrinkage resin.
- 2) The insulation resistance of the chip will degrade due to moisture absorption. Use a low moisture absorption resin.
- 3) Check carefully that the resin does not generate a decomposition gas or reaction gas during the curing process or during normal storage. Such gases may crack the chip capacitor or damage the device itself.


## Soldering Method

- 1) Ceramic is easily damaged by rapid heating or cooling. If some heat shock is unavoidable, preheat enough to limit the temperature difference (Delta T) to within 130 degree Celsius.
- 2) The product size 1.6×0.8mm to 3.2×1.6mm can be used in reflow and wave soldering, and the product size of bigger than 3.2×1.6mm, or smaller than 1.6×0.8mm, and capacitor arrays can be used in reflow.  
Circuit shortage and smoking can be created by using capacitors which are used neglecting the above caution.
- 3) Please see our recommended soldering conditions.
- 4) In case of using Sn-Zn Solder, please contact us in advance.
- 5) The following condition is recommended for spot heater application.

### • Recommended spot heater condition


Item	Condition
Distance	5mm min.
Angle	45°
Projection Temp.	400°C max.
Flow rate	Set at the minimum
Nozzle diameter	2φ to 4φ (Single hole type)
Application time	10 sec. max. (1206 and smaller) 30 sec. max. (1210 and larger)

### How to point spot heater




### Recommended Temperature Profile (Sn-3Ag-0.5Cu)

#### Reflow



- ① Minimize soldering time.
- ② Ensure that allowable temperature difference does not exceed 150°C.
- ③ Ensure that allowable temperature difference does not exceed 130°C for 3.2×2.5mm size or larger.


#### Wave



- ① Ensure that the chip capacitor is preheated adequately.
- ② Ensure that the temperature difference (ΔT) does not exceed 150°C.
- ③ Cool naturally after soldering.
- ④ Wave soldering is not applicable for chips with size of 3.2×2.5mm or larger of 1.0×0.5mm or smaller and capacitor arrays.


### Recommended Temperature Profile (62Sn Solder)

#### Reflow



- ① Minimize soldering time.
- ② Ensure that the temperature difference (ΔT) does not exceed 150°C.
- ③ Ensure that the temperature difference (ΔT) does not exceed 130°C for 3.2×2.5mm size or larger.
- ④ MLCC can withstand the above reflow conditions up to 3 times.

#### Wave



- ① Ensure that the chip capacitor is preheated adequately.
- ② Ensure that the temperature difference (ΔT) does not exceed 150°C.
- ③ Cool naturally after soldering.
- ④ Wave soldering is not applicable for chips with size of 3.2×2.5mm or larger of 1.0×0.5mm or smaller and capacitor arrays.

## Soldering iron

- 1) Temperature of iron chip  
1206 and smaller 350°C max.  
1210 and larger 280°C max.
- 2) Wattage  
80W max.
- 3) Tip shape of soldering iron  
φ3.0mm max.
- 4) Soldering Time  
3 sec. max.
- 5) Cautions
  - a) Pre-heating is necessary rapid heating must be avoided.  
Delta T ≤ 150°C
  - b) Avoid direct touching to capacitors.
  - c) Avoid rapid cooling after soldering. Natural cooling is recommended.

\*Consult as if it is difficult to keep the temperature 280°C max. for 1210 and larger MLCC'S.

### Circuit Design

1. Once application and assembly environments have been checked, the capacitor may be used in conformance with the rating and performance which are provided in both the catalog and the specifications. Use exceeding that which is specified may result in inferior performance or cause a short, open, smoking, or flaming to occur, etc.
2. Please consult the manufacturer in advance when the capacitor is used in devices such as: devices which deal with human life, i.e. medical devices; devices which are highly public orientated; and devices which demand a high standard of liability.  
Accident or malfunction of devices such as medical devices, space equipment and devices having to do with atomic power could generate grave consequence with respect to human lives or, possibly, a portion of the public. Capacitors used in these devices may require high reliability design different from that of general purpose capacitors.
3. Please use the capacitors in conformance with the operating temperature provided in both the catalog and the specifications.  
Be especially cautious not to exceed the maximum temperature. In the situation the maximum temperature set forth in both the catalog and specifications is exceeded, the capacitor's insulation resistance may deteriorate, power may suddenly surge and short-circuit may occur. The capacitor has a loss, and may self-heat due to equivalent series resistance when alternating electric current is passed therethrough. As this effect becomes especially pronounced in high frequency circuits, please exercise caution.  
When using the capacitor in a (self-heating) circuit, please make sure the surface of the capacitor remains under the maximum temperature for usage. Also, please make certain temperature rises remain below 20°C.
4. Please keep voltage under the rated voltage which is applied to the capacitor. Also, please make certain the peak voltage remains below the rated voltage when AC voltage is super-imposed to the DC voltage.  
In the situation where AC or pulse voltage is employed, ensure average peak voltage does not exceed the rated voltage.  
Exceeding the rated voltage provided in both catalog and specifications may lead to defective withstanding voltage or, in worst case situations, may cause the capacitor to smoke or flame.
5. When the capacitor is to be employed in a circuit in which there is continuous application of a high frequency voltage or a steep pulse voltage, even though it is within the rated voltage, please inquire to the manufacturer.  
In the situation the capacitor is to be employed using a high frequency AC voltage or a extremely fast rising pulse voltage, even though it is within the rated voltage, it is possible capacitor reliability will deteriorate.
6. It is a common phenomenon of high-dielectric products to have a deteriorated amount of static electricity due to the application of DC voltage.  
Due caution is necessary as the degree of deterioration varies depending on the quality of capacitor materials, capacity, as well as the load voltage at the time of operation.
7. Do not use the capacitor in an environment where it might easily exceed the respective provisions concerning shock and vibration specified in the catalog and specifications.  
In addition, it is a common piezo phenomenon of high dielectric products to have some voltage due to vibration or to have noise due to voltage change. Please contact sales in such case.
8. If the electrostatic capacity value of the delivered capacitor is within the specified tolerance, please consider this when designing the respective product in order that the assembled product function appropriately.
9. Please contact us upon using conductive adhesives.

### Storage

1. If the component is stored in minimal packaging (a heat-sealed or chuck-type plastic bag), the bag should be kept closed. Once the bag has been opened, reseal it or store it in a desiccator.
2. Keep storage place temperature +5 to +40 degree C, humidity 20 to 70% RH.
3. The storage atmosphere must be free of gas containing sulfur and chlorine. Also, avoid exposing the product to saline moisture. If the product is exposed to such atmospheres, the terminals will oxidize and solderability will be effected.
4. Precautions 1) to 3) apply to chip capacitors packaged in carrier tapes and bulk cases.
5. The solderability is assured for 12 months from our shipping date (six months for silver palladium) if the above storage precautions are followed.
6. Chip capacitors may crack if exposed to hydrogen (H<sub>2</sub>) gas while sealed or if coated with silicon, which generates hydrogen gas.

Safety application guideline and detailed information of electrical properties are also provided in Kyocera home page;

URL: <http://www.kyocera.co.jp/electronic/>