


Kyocera Ceramic Chip Capacitors are available for different applications as classified below:

| Series | Dielectric Options | Typical Applications | Features | Terminations | Available Size |
|--------|--|-------------------------------------|--|----------------|--|
| CM | C0G (NP0) X5R X7R *X6S *X7S Y5V | General Purpose | Wide Cap Range | Nickel Barrier | 0201, 0402, 0603 0805, 1206, 1210 1812 |
| CF | C0G (NP0) X7R | High Voltage & Power Circuits | High Voltage 250VDC, 630VDC 1000VDC, 2000VDC 3000VDC, 4000VDC | Nickel Barrier | 0805, 1206, 1210 1812, 2208, 1808 2220 |
| CT | C0G (NP0) X5R X7R Y5V | PLCC (Decoupling) | Low Profile | Nickel Barrier | 0402, 0603, 0805 1206, 1210 |
| DM | X7R | Automotive | Thermal shock Resistivity High Reliability | Nickel Barrier | 0603, 0805, 1206 |
| CA | C0G (NP0) X5R, X7R | Digital Signal Pass line | Reduction in Placing Costs | Nickel Barrier | 0405, 0508 |

* option

Dimensions



Tape & Reel

| Size | EIA CODE | JIS CODE | Dimensions (mm) | | | | | |
|------|----------|----------|-----------------|-----------|--------|--------|-------------|--------|
| | | | L | W | P min. | P max. | P to P min. | T max. |
| 03 | 0201 | 0603 | 0.6±0.03 | 0.3±0.03 | 0.13 | 0.23 | 0.20 | 0.33 |
| 05 | 0402 | 1005 | 1.0±0.05 | 0.5±0.05 | 0.15 | 0.35 | 0.30 | 0.55 |
| 105 | 0603 | 1608 | 1.6±0.10 | 0.8±0.10 | 0.20 | 0.60 | 0.50 | 0.90 |
| 21 | 0805 | 2012 | 2.0±0.10 | 1.25±0.10 | 0.20 | 0.75 | 0.70 | 1.35 |
| 316 | 1206 | 3216 | 3.2±0.20 | 1.60±0.15 | 0.30 | 0.85 | 1.40 | 1.75 |
| 32 | 1210 | 3225 | 3.2±0.20 | 2.50±0.20 | 0.30 | 1.00 | 1.40 | 2.70 |
| 42 | 1808 | 4520 | 4.5±0.20 | 2.00±0.20 | 0.15 | 0.85 | 2.60 | 2.20 |
| 43 | 1812 | 4532 | 4.5±0.30 | 3.20±0.20 | 0.30 | 1.10 | 2.00 | 3.00 |
| 52 | 2208 | 5720 | 5.7±0.40 | 2.00±0.20 | 0.15 | 0.85 | 4.20 | 2.20 |
| 55 | 2220 | 5750 | 5.7±0.40 | 5.00±0.40 | 0.30 | 1.40 | 2.50 | 2.70 |

- T (Thickness) depends on capacitance value.
Standard thickness is shown on the appropriate product pages.
- CA series (please refer applicable page)
- As for the size of the product specified individually, please contact us.

Bulk Cassette

| Size | EIA CODE | JIS CODE | L | W | T | P | | P to P |
|------|----------|----------|----------|----------|----------|------|------|--------|
| | | | | | | min. | max. | min. |
| 05 | 0402 | 1005 | 1.0±0.05 | 0.5±0.05 | 0.5±0.05 | 0.15 | 0.35 | 0.30 |
| 105 | 0603 | 1608 | 1.6±0.07 | 0.8±0.07 | 0.8±0.07 | 0.20 | 0.60 | 0.50 |
| 21 | 0805 | 2012 | 2.0±0.1 | 1.25±0.1 | 1.25±0.1 | 0.20 | 0.75 | 0.70 |

Note) Regarding support for Bulk cases, please contact us for further information.

Multilayer Ceramic Chip Capacitors

Ordering Information



KYOCERA PART NUMBER:

CM 21 X7R 104 K 50 A T □ □ □

SERIES CODE

CM = General Purpose CA = Capacitor Arrays
CF = High Voltage
CT = Low Profile
DM = Automotive

SIZE CODE

| SIZE | EIA (JIS) | SIZE | EIA (JIS) | SIZE | EIA (JIS) |
|------|---------------------|------|---------------|------|---------------------|
| 03 | = 0201 (0603) | 21 | = 0805 (2012) | 52 | = 2208 (5720) |
| 05 | = 0402 (1005) | 316 | = 1206 (3216) | 55 | = 2220 (5750) |
| 105 | = 0603 (1608) | 32 | = 1210 (3225) | D11 | = 0405 (1012)/ 2cap |
| F12 | = 0508 (1220)/ 4cap | 42 | = 1808 (4520) | D12 | = 0508 (1220)/ 2cap |
| | | 43 | = 1812 (4532) | | |

DIELECTRIC CODE

| CODE | EIA CODE | |
|------|-------------|--------------------|
| CG | = C0G (NPO) | X7S = X7S (Option) |
| X5R | = X5R | X6S = X6S (Option) |
| X7R | = X7R | Y5V = Y5V |

Negative dielectric types are available on request.

CAPACITANCE CODE

Capacitance expressed in pF. 2 significant digits plus number of zeros.

For Values < 10pF, Letter R denotes decimal point,

eg. 100000pF = 104 1.5pF = 1R5
0.1μF = 104 0.5pF = R50
4700pF = 472 100μF = 107

TOLERANCE CODE

| | | | |
|----------------------|------------------|----------|-----------------|
| A = ±0.05pF (option) | D = ±0.5pF | J = ±5% | Z = -20 to +80% |
| B = ±0.1pF (option) | F = ±1pF | K = ±10% | |
| C = ±0.25pF | G = ±2% (option) | M = ±20% | |

VOLTAGE CODE

| | | |
|-------------|--------------|----------------|
| 04 = 4VDC | 100 = 100VDC | 1000 = 1000VDC |
| 06 = 6.3VDC | 250 = 250VDC | 2000 = 2000VDC |
| 10 = 10VDC | 400 = 400VDC | 3000 = 3000VDC |
| 16 = 16VDC | 630 = 630VDC | 4000 = 4000VDC |
| 25 = 25VDC | | |
| 35 = 35VDC | | |
| 50 = 50VDC | | |

TERMINATION CODE

A = Nickel Barrier

PACKAGING CODE

| | |
|---------------------------------------|--|
| B = Bulk | L = 13" Reel Taping & 4mm Cavity pitch |
| C = Bulk Cassette (option) | H = 7" Reel Taping & 2mm Cavity pitch |
| T = 7" Reel Taping & 4mm Cavity pitch | N = 13" Reel Taping & 2mm Cavity pitch |

OPTION

Thickness max. value is indicated in CT series

EX. 125 → 1.25mm max.
095 → 0.95mm max.

Multilayer Ceramic Chip Capacitors

Temperature Characteristics and Tolerance



High Dielectric Constant

| EIA Dielectric | Temperature Range | ΔC max. |
|----------------|-------------------|-----------------|
| X5R | -55 to 85°C | ±15% |
| X7R | -55 to 125°C | |
| *X7S | -55 to 125°C | ±22% |
| *X6S | -55 to 105°C | |
| Y5V | -30 to 85°C | -82 to +22% |

* option

Temperature Compensation Type

| Electric Code Value (pF) | C0G | UΔ N750 | SL +350 to -1000 |
|--------------------------|-----|---------|------------------|
| 0.5 to 2.7 | CK | UK | SL |
| 3.0 to 3.9 | CJ | UJ | SL |
| 4.0 to 9.0 | CH | UJ | SL |
| ≥10 | CG | UJ | SL |

K = ±250ppm/°C, J = ±120ppm/°C, H = ±60ppm/°C, G = ±30ppm/°C
e.g. CG = 0±30ppm/°C

Note: All parts will be marked as "CG" but will conform to the above table.

Available Tolerances

Dielectric materials, capacitance values and tolerances are available in the following combinations only:

| EIA Dielectric | Tolerance | Capacitance |
|-------------------|----------------------------------|---------------------|
| C0G | C=±0.25pF D=±0.50pF F=±1pF | *1 <10pF |
| | *3 A=±0.05pF B=±0.1pF | <0.5pF ≤5pF |
| | *3 G=±2% J=±5% K=±10% | ≥10pF E12 Series |
| | *2 K=±10% M=±20% | E6 Series |
| X5R X6R X7R | | |
| Y5V | Z=-20% to +80% | E3 Series |

Note:

*1 Nominal values below 10pF are available in the standard values of 0.5pF, 1.0pF, 1.5pF, 2.0pF, 3.0pF, 4.0pF, 5.0pF, 6.0pF, 7.0pF, 8.0pF, 9.0pF

*2 J = ±5% for X7R (X5R) is available on request.

*3 option

E Standard Number

| E3 | E6 | E12 | E24 (Option) | |
|-----|-----|-----|--------------|-----|
| 1.0 | 1.0 | 1.0 | 1.0 | 1.1 |
| | | 1.2 | 1.2 | 1.3 |
| | 1.5 | 1.5 | 1.5 | 1.6 |
| | | 1.8 | 1.8 | 2.0 |
| 2.2 | 2.2 | 2.2 | 2.2 | 2.4 |
| | | 2.7 | 2.7 | 3.0 |
| | 3.3 | 3.3 | 3.3 | 3.6 |
| | | 3.9 | 3.9 | 4.3 |
| 4.7 | 4.7 | 4.7 | 4.7 | 5.1 |
| | | 5.6 | 5.6 | 6.2 |
| | 6.8 | 6.8 | 6.8 | 7.5 |
| | | 8.2 | 8.2 | 9.1 |

Features

We offer a diverse product line ranging from ultra-compact (0.6×0.3mm) to large (4.3×3.2mm) components configured for a variety of temperature characteristics, rated voltages, and packages. We offer the choice and flexibility for almost any applications.

Applications

This standard type is ideal for use in a wide range of applications, from commercial to industrial equipment.

Temperature Compensation Dielectric

| Size (EIA Code) | CM03 (0201) | | | | | CM05 (0402) | | | CM105 (0603) | | CM21 (0805) | | | |
|---|----------------|----|------------|----|----|----------------|------------|----|-----------------|-----|----------------|----|----|-----|
| Temperature Characteristics | C Δ | | U Δ | | SL | C Δ | U Δ | SL | C Δ | | C Δ | | | |
| Rated Voltage (VDC) Capacitance (pF) | 25 | 50 | 16 | 25 | 25 | 50 | 50 | 50 | 50 | 100 | 16 | 25 | 50 | 100 |
| R20 0.2 | | | | | | | | | | | | | | |
| R50 0.5 | | | | | | | | | | | | | | |
| 1R0 1.0 | | | A | | | | | | | | | | | |
| 1R5 1.5 | | | | | | | | | | | | | | |
| 2.0 | | | | | | | | | | | | | | |
| 3.0 | | | | | | | | | | | | | | |
| 4.0 | | | | | | | | | | | | | | |
| 5.0 | | | | | | | | | | | | | | |
| 6.0 | | | | | | | | | | | | | | |
| 7.0 | | | | | | | | | | | | | | |
| 8.0 | | | | | | | | | | | | | | |
| 9.0 | | | | | | | | | | | | | | |
| 100 10 | A | | | | | | | | | | | | | |
| 120 12 | | | | | | | | | | | | | | |
| 15 15 | | | | | | | | | | | | | | |
| 18 18 | | | | | | | | | | | | | | |
| 22 22 | | | | | | | | | | | | | | |
| 27 27 | | | | | | | | | | | | | | |
| 33 33 | | | | | | | | | | | | | | |
| 39 39 | | | | | | | | | | | | | | |
| 47 47 | | | | | | | | | | | | | | |
| 56 56 | | | | | | | | | | | | | | |
| 68 68 | | | | | | | | | | | | | | |
| 82 82 | | | | | | | | | | | | | | |
| 101 100 | | | | | | | | | | | | | | |
| 121 120 | | | | | | | | | | | | | | |
| 150 150 | | | | | | | | | | | | | | |
| 180 180 | | | | | | | | | | | | | | |
| 220 220 | | | | | | | | | | | | | | |
| 270 270 | | | | | | | | | | | | | | |
| 330 330 | | | | | | | | | | | | | | |
| 390 390 | | | | | | | | | | | | | | |
| 470 470 | | | | | | | | | | | | | | |
| 560 560 | | | | | | | | | | | | | | |
| 680 680 | | | | | | | | | | | | | | |
| 820 820 | | | | | | | | | | | | | | |
| 102 1000 | | | | | | | | | | | | | | |
| 122 1200 | | | | | | | | | | | | | | |
| 1500 1500 | | | | | | | | | | | | | | |
| 1800 1800 | | | | | | | | | | | | | | |
| 2200 2200 | | | | | | | | | | | | | | |
| 2700 2700 | | | | | | | | | | | | | | |
| 3300 3300 | | | | | | | | | | | | | | |
| 3900 3900 | | | | | | | | | | | | | | |
| 4700 4700 | | | | | | | | | | | | | | |
| 5600 5600 | | | | | | | | | | | | | | |
| 6800 6800 | | | | | | | | | | | | | | |
| 8200 8200 | | | | | | | | | | | | | | |
| 103 10000 | | | | | | | | | | | | | | |
| 123 12000 | | | | | | | | | | | | | | |
| 15000 15000 | | | | | | | | | | | | | | |
| 18000 18000 | | | | | | | | | | | | | | |

Thickness and standard package quantity

| Size | *03 | *05 | 105 | *105 | 21, 316, 32 | | | | | | | | |
|-----------------------|-----------|-----------|-----------|-----------|-------------|-----------|-----------|-----------|-----------|------------|------------|----------|----------|
| Thickness (mm) | A | B | C | C | D | E | F | G | H | I | J | K | L |
| | 0.3±0.03 | 0.5±0.05 | 0.8±0.1 | 0.8±0.1 | 0.6±0.1 | 0.85±0.1 | 1.15±0.1 | 1.25±0.1 | 1.4 max. | 1.6 max. | 1.6±0.15 | 2.0±0.2 | 2.5±0.2 |
| Taping (180 dia reel) | 15kp (P8) | 10kp (P8) | 4kp (P8) | 8kp (P8) | 4kp (P8) | 4kp (P8) | 3kp (E8) | 3kp (E8) | 3kp (E8) | 2.5kp (E8) | 2.5kp (E8) | 2kp (E8) | 1kp (E8) |
| Taping (330 dia reel) | 50kp (P8) | 50kp (P8) | 10kp (P8) | 20kp (P8) | 10kp (P8) | 10kp (P8) | 10kp (E8) | 10kp (E8) | 10kp (E8) | 5kp (E8) | 5kp (E8) | 5kp (E8) | — |

| Size | 43 | | | | <div>Note: P8 = 8mm width paper tape E8 = 8mm width plastic tape E12 = 12mm width plastic tape</div> <div>* Carrier tape 2mm pitch from one capacitor to another.</div> |
|-----------------------|-----------|-----------|-------------|-------------|---|
| Thickness (mm) | J | K | L | M | |
| | 1.6±0.15 | 2.0±0.2 | 2.5±0.2 | 2.8±0.2 | |
| Taping (180 dia reel) | 1kp (E12) | 1kp (E12) | 0.5kp (E12) | 0.5kp (E12) | |
| Taping (330 dia reel) | — | — | — | — | |

X5R Dielectric

| Size (EIA Code) | CM03 (0201) | | | | | CM05 (0402) | | | | | | CM105 (0603) | | | | | | CM21 (0805) | | | | | | | | |
|---|----------------|-----|----|----|----|----------------|-----|----|----|----|----|-----------------|-----|----|----|----|----|----------------|-----|----|----|----|----|--|--|--|
| Rated Voltage (VDC) Capacitance (pF) | 4 | 6.3 | 10 | 16 | 25 | 4 | 6.3 | 10 | 16 | 25 | 50 | 4 | 6.3 | 10 | 16 | 25 | 50 | 4 | 6.3 | 10 | 16 | 25 | 50 | | | |
| 101 100 | | | | | | | | | | | | | | | | | | | | | | | | | | |
| 151 150 | | | | | A | | | | | | B | | | | | | | | | | | | | | | |
| 220 | | | | | | | | | | | | | | | | | | | | | | | | | | |
| 330 | | | | | | | | | | | | | | | | | | | | | | | | | | |
| 470 | | | | | A | | | | | | B | | | | | | | | | | | | | | | |
| 680 | | | | | | | | | | | | | | | | | | | | | | | | | | |
| 102 1000 | | | | | | | | | | | | | | | | | | | | | | | | | | |
| 152 1500 | | | A | A | | | | | | | B | | | | | | | | | | | | | | | |
| 2200 | | | | | | | | | | | | | | | | | | | | | | | | | | |
| 3300 | | | | | | | | | | | | | | | | | | | | | | | | | | |
| 4700 | | | A | | A | | | | | | B | | | | | | C | | | | | | | | | |
| 6800 | | | | | | | | | | | | | | | | | | | | | | | | | | |
| 103 10000 | | | | | | | | | | | | | | | | | | | | | | | | | | |
| 153 15000 | | | | | | | | | | | B | | | | | | C | | | | | | | | | |
| 22000 | | | | | | | | | | | | | | | | | | | | | | | | | | |
| 33000 | | | | | | | | | | | | | | | | | | | | | | | | | | |
| 47000 | | | | | | | | | | | B | | | | | | C | | | | | | | | | |
| 68000 | | | | | | | | | | | | | | | | | | | | | | | | | | |
| 104 100000 | | | | | | | | | | | | | | | | | | | | | | | | | | |
| 154 150000 | | | | | | | | | | | | | | | | | C | | | | | | | | | |
| 220000 | | | | | | | | | | | | | | | | | | | | | | | | | | |
| 330000 | | | | | | | | | | | | | | | | | | | | | | | | | | |
| 470000 | | | | | | | | | | | | | | | | | C | | | | | | | | | |
| 680000 | | | | | | | | | | | | | | | | | | | | | | | | | | |
| 105 1000000 | | | | | | | | | | | | | | | | | | | | | | | | | | |
| 155 1500000 | | | | | | | | | | | | | | | | | C | | | | | | | | | |
| 2200000 | | | | | | | | | | | | | | | | | | | | | | | | | | |
| 3300000 | | | | | | | | | | | | | | | | | | | | | | | | | | |
| 4700000 | | | | | | | | | | | | | | | | | C | | | | | | | | | |
| 6800000 | | | | | | | | | | | | | | | | | | | | | | | | | | |
| 106 10000000 | | | | | | | | | | | | | | | | | | | | | | | | | | |
| 156 15000000 | | | | | | | | | | | | | | | | | | | | | | | | | | |
| 22000000 | | | | | | | | | | | | | | | | | | | | | | | | | | |
| 476 33000000 | | | | | | | | | | | | | | | | | | | | | | | | | | |
| 47000000 | | | | | | | | | | | | | | | | | | | | | | | | | | |

| Size (EIA Code) | CM316 (1206) | | | | | CM32 (1210) | | | | | | CM43 (1812) | |
|---|-----------------|----|----|----|----|----------------|-----|----|----|----|----|----------------|----|
| Rated Voltage (VDC) Capacitance (pF) | 6.3 | 10 | 16 | 25 | 50 | 4 | 6.3 | 10 | 16 | 25 | 50 | 6.3 | 50 |
| 104 100000 | | | | | | | | | | | | | |
| 220000 | | | | | | | | | | | | | |
| 470000 | | | | | | | | | | | | | |
| 105 1000000 | | | | | | | | | | | | | |
| 2200000 | | | | | | | | | | | | | |
| 4700000 | | | | | | | | | | | | | |
| 106 10000000 | | | | | | | | | | | | | |
| 22000000 | | | | | | | | | | | | | |
| 47000000 | | | | | | | | | | | | | |
| 107 100000000 | | | | | | | | | | | | | |

Optional Spec.

Thickness and standard package quantity

| Size | *03 | *05 | 105 | *105 | 21, 316, 32 | | | | | | | | |
|-----------------------|-----------|-----------|-----------|-----------|-------------|-----------|-----------|-----------|-----------|------------|------------|----------|----------|
| Thickness (mm) | A | B | C | C | D | E | F | G | H | I | J | K | L |
| | 0.3±0.03 | 0.5±0.05 | 0.8±0.1 | 0.8±0.1 | 0.6±0.1 | 0.85±0.1 | 1.15±0.1 | 1.25±0.1 | 1.4 max. | 1.6 max. | 1.6±0.15 | 2.0±0.2 | 2.5±0.2 |
| Taping (180 dia reel) | 15kp (P8) | 10kp (P8) | 4kp (P8) | 8kp (P8) | 4kp (P8) | 4kp (P8) | 3kp (E8) | 3kp (E8) | 3kp (E8) | 2.5kp (E8) | 2.5kp (E8) | 2kp (E8) | 1kp (E8) |
| Taping (330 dia reel) | 50kp (P8) | 50kp (P8) | 10kp (P8) | 20kp (P8) | 10kp (P8) | 10kp (P8) | 10kp (E8) | 10kp (E8) | 10kp (E8) | 5kp (E8) | 5kp (E8) | 5kp (E8) | — |

| Size | 43 | | | |
|-----------------------|-----------|-----------|-------------|-------------|
| Thickness (mm) | J | K | L | M |
| | 1.6±0.15 | 2.0±0.2 | 2.5±0.2 | 2.8±0.2 |
| Taping (180 dia reel) | 1kp (E12) | 1kp (E12) | 0.5kp (E12) | 0.5kp (E12) |
| Taping (330 dia reel) | — | — | — | — |

Note: P8 = 8mm width paper tape
E8 = 8mm width plastic tape
E12 = 12mm width plastic tape

* Carrier tape 2mm pitch from one capacitor to another.

X7R, Dielectric

| Size (EIA Code) | CM03 (0201) | | | CM05 (0402) | | | CM105 (0603) | | | | | | CM21 (0805) | | | | | |
|---|----------------|----|----|----------------|----|----|-----------------|----|----|----|----|-----|----------------|----|----|----|----|-----|
| Rated Voltage (VDC) Capacitance (pF) | 10 | 16 | 25 | 16 | 25 | 50 | 6.3 | 10 | 16 | 25 | 50 | 100 | 6.3 | 10 | 16 | 25 | 50 | 100 |
| 101 100 | | | | | | | | | | | | | | | | | | |
| 151 150 | | A | A | | | | | | | | | | | | | | | |
| 220 | | | | | | | | | | | | | | | | | | |
| 330 | | | | | | | | | | | | | | | | | | |
| 470 | | | | | | | | | | | | | | | | | | |
| 680 | | | | | | | | | | | | | | | | | | |
| 102 1000 | | | | | | | | | | | | | | | | | | |
| 152 1500 | A | | | | | | | | | | | | | | | | | |
| 2200 | | | | | | | | | | | | | | | | | | |
| 3300 | | | | | | | | | | | | | | | | | | |
| 4700 | | | | | | | | | | | | | | | | | | |
| 6800 | | | | | | | | | | | | | | | | | | |
| 103 10000 | | | | | | | | | | | | | | | | | | |
| 153 15000 | | | | | | | | | | | | | | | | | | |
| 22000 | | | | | | | | | | | | | | | | | | |
| 33000 | | | | | | | | | | | | | | | | | | |
| 47000 | | | | | | | | | | | | | | | | | | |
| 68000 | | | | | | | | | | | | | | | | | | |
| 104 100000 | | | | | | | | | | | | | | | | | | |
| 154 150000 | | | | | | | | | | | | | | | | | | |
| 220000 | | | | | | | | | | | | | | | | | | |
| 330000 | | | | | | | | | | | | | | | | | | |
| 470000 | | | | | | | | | | | | | | | | | | |
| 680000 | | | | | | | | | | | | | | | | | | |
| 105 1000000 | | | | | | | | | | | | | | | | | | |
| 155 1500000 | | | | | | | | | | | | | | | | | | |
| 2200000 | | | | | | | | | | | | | | | | | | |
| 3300000 | | | | | | | | | | | | | | | | | | |
| 4700000 | | | | | | | | | | | | | | | | | | |
| 106 10000000 | | | | | | | | | | | | | | | | | | |

| Size (EIA Code) | CM316 (1206) | | | | | | CM32 (1210) | | | | | CM43 (1812) | |
|---|-----------------|----|----|----|----|-----|----------------|----|----|----|-----|----------------|-----|
| Rated Voltage (VDC) Capacitance (pF) | 6.3 | 10 | 16 | 25 | 50 | 100 | 10 | 16 | 25 | 50 | 100 | 50 | 100 |
| 103 10000 | | | | | | | | | | | | | |
| 22000 | | | | | | | | | | | | | |
| 47000 | | | | | | | | | | | | | |
| 104 100000 | | | | | | | | | | | | | |
| 220000 | | | | | | | | | | | | | |
| 470000 | | | | | | | | | | | | | |
| 105 1000000 | | | | | | | | | | | | | |
| 2200000 | | | | | | | | | | | | | |
| 4700000 | | | | | | | | | | | | | |
| 106 10000000 | | | | | | | | | | | | | |
| 22000000 | | | | | | | | | | | | | |

Optional Spec.

Y5V Dielectric

| Size (EIA Code) | CM03 (0201) | | | CM05 (0402) | | | CM105 (0603) | | | | CM21 (0805) | | | | CM316 (1206) | | | CM32 (1210) | | |
|---|----------------|----|----|----------------|----|----|-----------------|----|----|----|----------------|----|----|----|-----------------|----|----|----------------|----|----|
| Rated Voltage (VDC) Capacitance (pF) | 6.3 | 10 | 10 | 16 | 25 | 50 | 10 | 16 | 25 | 50 | 10 | 16 | 25 | 50 | 10 | 16 | 25 | 10 | 16 | 25 |
| 102 1000 | | A | | | | | | | | | | | | | | | | | | |
| 2200 | | | | | | | | | | | | | | | | | | | | |
| 4700 | | | | | | | | | | | | | | | | | | | | |
| 103 10000 | A | | | | | | | | | | | | | | | | | | | |
| 22000 | | | | | | | | | | | | | | | | | | | | |
| 47000 | | | | | | | | | | | | | | | | | | | | |
| 104 100000 | | | | | | | | | | | | | | | | | | | | |
| 220000 | | | | | | | | | | | | | | | | | | | | |
| 470000 | | | | | | | | | | | | | | | | | | | | |
| 105 1000000 | | | | | | | | | | | | | | | | | | | | |
| 2200000 | | | | | | | | | | | | | | | | | | | | |
| 4700000 | | | | | | | | | | | | | | | | | | | | |
| 106 10000000 | | | | | | | | | | | | | | | | | | | | |
| 22000000 | | | | | | | | | | | | | | | | | | | | |
| 47000000 | | | | | | | | | | | | | | | | | | | | |

Thickness and standard package quantity


| Size | *03 | *05 | 105 | *105 | 21, 316, 32 | | | | | | | | |
|-----------------------|-----------|-----------|-----------|-----------|-------------|-----------|-----------|-----------|-----------|------------|------------|----------|----------|
| Thickness (mm) | A | B | C | C | D | E | F | G | H | I | J | K | L |
| | 0.3±0.03 | 0.5±0.05 | 0.8±0.1 | 0.8±0.1 | 0.6±0.1 | 0.85±0.1 | 1.15±0.1 | 1.25±0.1 | 1.4 max. | 1.6 max. | 1.6±0.15 | 2.0±0.2 | 2.5±0.2 |
| Taping (180 dia reel) | 15kp (P8) | 10kp (P8) | 4kp (P8) | 8kp (P8) | 4kp (P8) | 4kp (P8) | 3kp (E8) | 3kp (E8) | 3kp (E8) | 2.5kp (E8) | 2.5kp (E8) | 2kp (E8) | 1kp (E8) |
| Taping (330 dia reel) | 50kp (P8) | 50kp (P8) | 10kp (P8) | 20kp (P8) | 10kp (P8) | 10kp (P8) | 10kp (E8) | 10kp (E8) | 10kp (E8) | 5kp (E8) | 5kp (E8) | 5kp (E8) | — |

| Size | 43 | | | |
|-----------------------|-----------|-----------|-------------|-------------|
| Thickness (mm) | J | K | L | M |
| | 1.6±0.15 | 2.0±0.2 | 2.5±0.2 | 2.8±0.2 |
| Taping (180 dia reel) | 1kp (E12) | 1kp (E12) | 0.5kp (E12) | 0.5kp (E12) |
| Taping (330 dia reel) | — | — | — | — |


Note: P8 = 8mm width paper tape
E8 = 8mm width plastic tape
E12 = 12mm width plastic tape

* Carrier tape 2mm pitch from one capacitor to another.


Capacitance-Temperature (temperature compensation)




Aging (change of capacitance over time)




Capacitance-Temperature (high dielectric constant)




Impedance-Frequency



DC Bias



AC Voltage



Please verify individual characteristics at the design stage to ensure total suitability.

Test Conditions and Specifications for Temperature Compensation type (C Δ to U Δ • SL Characteristics)

| Test Items | | Specifications (C: nominal capacitance) | Test Conditions | | | | | | | | | | | |
|---------------------------------|---|--|---|-------------|---------|------------|--------------|--------------|------------|-------------|-----------|---|--------------|-----------|
| Capacitance Value | | Within tolerance | <table><tr><td>C≤1000pF</td><td>1MHz±10%</td><td rowspan="2">0.5 to 5Vrms</td></tr><tr><td>C>1000pF</td><td>1kHz±10%</td></tr></table> | | | C≤1000pF | 1MHz±10% | 0.5 to 5Vrms | C>1000pF | 1kHz±10% | | | | |
| C≤1000pF | 1MHz±10% | 0.5 to 5Vrms | | | | | | | | | | | | |
| C>1000pF | 1kHz±10% | | | | | | | | | | | | | |
| Q | | C≥30pF: Q≥1000 C<30pF: Q≥400+20C | | | | | | | | | | | | |
| Insulation resistance (IR) (*5) | | 10,000MΩ or 500MΩ • μF min., whichever is less | Measured after the rated voltage is applied for one minute at normal room temperature and humidity. (*3) | | | | | | | | | | | |
| Dielectric resistance (*5) | | No problem observed | (*1) Apply 3 times of the rated voltage for 1 to 5 seconds. | | | | | | | | | | | |
| Appearance | | No problem observed | Microscope (10×magnification) | | | | | | | | | | | |
| Termination strength | | No problem observed | Apply a sideward force of 500g (5N) (*2) to a PCB-mounted sample. | | | | | | | | | | | |
| Bending strength | | No mechanical damage at 1mm bent | Glass epoxy PCB (t=1.6mm); fulcrum Spacing: 90mm; for 10 seconds. | | | | | | | | | | | |
| Vibration test | Appearance | No significant change is detected | Vibration frequency: 10 to 55 (Hz) Amplitude: 1.5mm Sweeping condition: 10→55→10Hz/ min. In X, Y and Z directions: 2 hours each Total 6 hours | | | | | | | | | | | |
| | ΔC | Within tolerance | | | | | | | | | | | | |
| | Q | C≥30pF: Q≥1000 C<30pF: Q≥400+20C | | | | | | | | | | | | |
| Soldering heat resistance | Appearance | No significant change is detected | Soak the sample in 260°C±5°C solder for 10±0.5 seconds and place in a room at normal temperature and humidity; measure after 24±2 hours. (Preheating Conditions) <table><tr><th>Order</th><th>Temperature</th><th>Time</th></tr><tr><td>1</td><td>80 to 100°C</td><td>2 minutes</td></tr><tr><td>2</td><td>150 to 200°C</td><td>2 minutes</td></tr></table> | | | Order | Temperature | Time | 1 | 80 to 100°C | 2 minutes | 2 | 150 to 200°C | 2 minutes |
| | Order | Temperature | | | | Time | | | | | | | | |
| | 1 | 80 to 100°C | | | | 2 minutes | | | | | | | | |
| | 2 | 150 to 200°C | | | | 2 minutes | | | | | | | | |
| | ΔC | ±2.5% or ±0.25pF max., whichever is larger | | | | | | | | | | | | |
| Q | C≥30pF: Q≥1000 C<30pF: Q≥400+20C | | | | | | | | | | | | | |
| IR (*5) | 10,000MΩ or 500MΩ • μF min., whichever is smaller | | | | | | | | | | | | | |
| Withstand voltage(*5) | Resists without problem | | | | | | | | | | | | | |
| Solderability | | Ni/ Br termination: 90% min. | Soaking Condition | | | | | | | | | | | |
| | | | <table><tr><td>Sn63 Solder</td><td>235±5°C</td><td>2±0.5 sec.</td></tr><tr><td>Sn-3Ag-0.5Cu</td><td>245±5°C</td><td>3±0.5 sec.</td></tr></table> | Sn63 Solder | 235±5°C | 2±0.5 sec. | Sn-3Ag-0.5Cu | 245±5°C | 3±0.5 sec. | | | | | |
| Sn63 Solder | 235±5°C | 2±0.5 sec. | | | | | | | | | | | | |
| Sn-3Ag-0.5Cu | 245±5°C | 3±0.5 sec. | | | | | | | | | | | | |
| Temperature cycle | Appearance | No significant change is detected | (Cycle) Normal room temperature (3 min.) → Lowest operation temperature (30 min.) → Normal room temperature (3 min.) → Highest operation temperature (30 min.) → After five cycles, measure after 24±2 hours. | | | | | | | | | | | |
| | ΔC | ±2.5% or ±0.25pF max., whichever is larger | | | | | | | | | | | | |
| | Q | C≥30pF: Q≥1000 C<30pF: Q≥400+20C | | | | | | | | | | | | |
| | IR (*5) | 10,000MΩ or 500MΩ • μF min., whichever is smaller | | | | | | | | | | | | |
| | Withstand voltage(*5) | Resists without problem | | | | | | | | | | | | |
| Load humidity test (*4) | Appearance | No significant change is detected | After applying rated voltage for 500±24/ –0 hours in pre-condition at 40±2°C, humidity 90 to 95%RH allow parts to stabilize for 48±4 hours, at room temperature before making measurements. | | | | | | | | | | | |
| | ΔC | ±7.5% or ±0.75pF max., whichever is larger | | | | | | | | | | | | |
| | Q | C≥30pF: Q≥200 C<30pF: Q≥100+10C/ 3 | | | | | | | | | | | | |
| | IR (*5) | 500MΩ or 25MΩ • μF min., whichever is smaller | | | | | | | | | | | | |
| High-temperature with loading | Appearance | No significant change is detected | After applying (*1) twice of the rated voltage at a temperature of 125±3°C for 1000±48/ –0 hours, measure the sample after storing 24±2 hours. | | | | | | | | | | | |
| | ΔC | ±3% or ±0.3pF max., whichever is larger | | | | | | | | | | | | |
| | Q | C≥30pF: Q≥350 10pF≤C<30pF: Q≥275+5C/ 2 C<10pF: Q≥200+10C | | | | | | | | | | | | |
| | IR (*5) | 1,000MΩ or 50MΩ • μF min., whichever is smaller | | | | | | | | | | | | |

*1 For the CF series, use 1.5 times when the rated voltage is 250V; use/ 1.2 times when the rated voltage exceeds 630V.

*2 2N at 0201 Size

*3 Apply 500V for 1 minute in case the rated voltage is 630V or higher.

*4 Except CF series.

*5 The charge and discharge current of the capacitor must not exceed 50mA.

Multilayer Ceramic Chip Capacitors

Test Conditions and Standards



Test Conditions and Specifications for High Dielectric Type (X5R, X7R, Y5V)

| Test Items | | Specifications | | Test Conditions | | | | | | | | | |
|----------------------------------|---|---|---|---|-------------|-------------|------------|--------------|-------------|-------------|--------|--------------|-------------|
| | | X7R/ X5R | Y5V | | | | | | | | | | |
| Capacitance Value | | Within tolerance | | Do previous treatment (*8, *14) | | | | | | | | | |
| tanδ (%) | | 2.5% max., 3.5% max. (*2), 7.0% max. (*12) 5.0% max. (*3), 7.5% max. (*17) | 5.0% max., 7.0% max. (*13) 9.0% max. (*4), 12.5% max. (*5) | <table><tr><th>Capacitance</th><th>Fire</th><th>Vol</th></tr><tr><td>C≤10μF</td><td>1kHz±10%</td><td>1.0±0.2Vrms</td></tr><tr><td>C>10μF</td><td>120Hz±10%</td><td>0.5±0.2Vrms</td></tr></table> | Capacitance | Fire | Vol | C≤10μF | 1kHz±10% | 1.0±0.2Vrms | C>10μF | 120Hz±10% | 0.5±0.2Vrms |
| | | | | Capacitance | Fire | Vol | | | | | | | |
| | | | | C≤10μF | 1kHz±10% | 1.0±0.2Vrms | | | | | | | |
| C>10μF | 120Hz±10% | 0.5±0.2Vrms | | | | | | | | | | | |
| Insulation resistance (IR) (*15) | | 10,000MΩ or 500MΩ • μF min., whichever is less | | Measured after the rated voltage is applied for 2 minutes at normal room temperature and humidity. (*10) | | | | | | | | | |
| Dielectric resistance (*15) | | No problem observed | | (*1) Apply 2.5 times of the rated voltage for 1 to 5 seconds. | | | | | | | | | |
| Appearance | | No problem observed | | Microscope (10×magnification) | | | | | | | | | |
| Termination strength (*6) | | No problem observed | | Apply a sideward force of 500g (5N) (*16) to a PCB-mounted sample. | | | | | | | | | |
| Bending strength test (*6) | | No problem observed at 1mm bent | | Glass epoxy PCB (*03, 05 type and CA Series: T=0.8mm); fulcrum Spacing: 90mm; for 10 seconds. | | | | | | | | | |
| Vibration test | Appearance | No significant change is detected | | Vibration frequency: 10 to 55 (Hz) Amplitude: 1.5mm Sweeping condition: 10→55→10Hz/ min. In X, Y and Z directions: 2 hours each Total 6 hours | | | | | | | | | |
| | ΔC | Within tolerance | | | | | | | | | | | |
| | tanδ (%) | Satisfies the initial value | | | | | | | | | | | |
| Soldering heat resistance | Appearance | No significant change is detected | | Do previous treatment (*8) Soak the sample in 260°C±5°C solder for 10±0.5 seconds and place in a room at normal temperature and humidity; measure after 48±4 hours. (Preheating Conditions) <table><tr><th>Order</th><th>Temperature</th><th>Time</th></tr><tr><td>1</td><td>80 to 100°C</td><td>2 minutes</td></tr><tr><td>2</td><td>150 to 200°C</td><td>2 minutes</td></tr></table> | Order | Temperature | Time | 1 | 80 to 100°C | 2 minutes | 2 | 150 to 200°C | 2 minutes |
| | Order | Temperature | Time | | | | | | | | | | |
| | 1 | 80 to 100°C | 2 minutes | | | | | | | | | | |
| | 2 | 150 to 200°C | 2 minutes | | | | | | | | | | |
| | ΔC | Within ±7.5% | Within ±20% | | | | | | | | | | |
| tanδ (%) | Satisfies the initial value | | | | | | | | | | | | |
| IR (*15) | 10,000MΩ or 500MΩ • μF min., whichever is smaller | | | | | | | | | | | | |
| | Withstand voltage (*15) | Resists without problem | | | | | | | | | | | |
| Solderability | | Ni/ Br termination: 90% min. | | Soaking Condition <table><tr><td>Sn63 Solder</td><td>235±5°C</td><td>2±0.5 sec.</td></tr><tr><td>Sn-3Ag-0.5Cu</td><td>245±5°C</td><td>3±0.5 sec.</td></tr></table> | Sn63 Solder | 235±5°C | 2±0.5 sec. | Sn-3Ag-0.5Cu | 245±5°C | 3±0.5 sec. | | | |
| Sn63 Solder | 235±5°C | 2±0.5 sec. | | | | | | | | | | | |
| Sn-3Ag-0.5Cu | 245±5°C | 3±0.5 sec. | | | | | | | | | | | |
| Temperature cycle | Appearance | No significant change is detected | | Do previous treatment (*8) (Cycle) Normal room temperature (3 min.) → Lowest operation temperature (30 min.) → Normal room temperature (3 min.) → Highest operation temperature (30 min.) → After five cycles, measure after 48±4hours. | | | | | | | | | |
| | ΔC | Within ±7.5% | Within ±20% | | | | | | | | | | |
| | tanδ (%) | Satisfies the initial value | | | | | | | | | | | |
| | IR (*15) | 10,000MΩ or 500MΩ • μF min., whichever is smaller | | | | | | | | | | | |
| | Withstand voltage (*15) | Resists without problem | | | | | | | | | | | |
| Load humidity test (*11) | Appearance | No significant change is detected | | Do previous treatment (*9) After applying rated voltage at 40±2°C and humidity 90 to 95%RH, for 500+24/ –0 hours and keep at room condition for 48±4 hours then measure and check the specification limits. | | | | | | | | | |
| | ΔC | Within ±12.5% | Within ±30% | | | | | | | | | | |
| | tanδ (%) | 200% max. of initial value | 150% max. of initial value | | | | | | | | | | |
| | IR (*15) | 500MΩ or 25MΩ • μF min., whichever is smaller | | | | | | | | | | | |
| High-temperature with loading | Appearance | No significant change is detected | | Do previous treatment (*9) After applying twice (*7) of the rated voltage at the highest operating temperature for 1000+48/ –0 hours, measure the sample after storing 48±4 hours. | | | | | | | | | |
| | ΔC | Within ±12.5% | Within ±30% | | | | | | | | | | |
| | tanδ (%) | 200% max. of initial value | 150% max. of initial value | | | | | | | | | | |
| | IR (*15) | 1,000MΩ or 50MΩ • μF min., whichever is smaller | | | | | | | | | | | |

*1 Use 1.5 times when the rated voltage is 250V or over.
Use 1.2 times when the rated voltage is 630V or over.

*2 X7R 16V/ 25V type.

*3 Apply to X5R16V/ 25V type, X7R 6.3V/ 10V type.

*4 Apply to Y5V 16V type, CM32Y5V335 to 106 (25V Type).

*5 Apply to Y5V 6.3V/ 10V type. Apply 16% max. to CM21Y5V106/ CM316Y5V226.

*6 Exclude CT series with thickness of less than 0.66mm and CA series.

*7 Use 1.5 times when the rated voltage is 4V/ 6.3V/ 10V/ 250V and 100V (32X7R474/ 43X7R105/ 55X7R105).

Use 1.2 times when the rated voltage is 630V or over.

*8 Keep specimen at 150°C+0/ -10°C for one hour, leave specimen at room ambient for 48±4 hours.

*9 Apply the same test condition for one hour, then leave the specimen at room ambient for 48±4 hours.

*10 For the CF series over 630V, apply 500V for 1 minute at room ambient.

*11 Except CF series.

*12 Apply to X5R 10V type.

*13 Apply to 25V series of CM105Y5V154 over, CM21Y5V105 over, 316Y5V155 over.

*14 Measurement condition 1kHz, 1Vrms for Y5V, C<47μF type.

*15 The charge/ discharge current of the capacitor must not exceed 50mA.

*16 2N at 0201 Size

*17 Apply to X5R 4V and 6.3V type.


* The above test conditions and standards do not apply to products with optional specifications.

Multilayer Ceramic Chip Capacitors Packaging Options



Tape and Reel

• Reel



Reel


(Unit: mm)

| Code Reel | A | B | C | D |
|------------------------------|-----------------------------------|----------------|----------------|--------|
| 7-inch Reel (CODE: T, H) | 180 ⁺⁰ _{-2.0} | φ60 min. | 13±0.5 | 21±0.8 |
| 13-inch Reel (CODE: L, N) | 330±2.0 | φ100±1.0 | | |
| Code Reel | E | W ₁ | W ₂ | R |
| 7-inch Reel (CODE: T, H) | 2.0±0.5 | 10.0±1.5 | 16.5 max. | 1.0 |
| 13-inch Reel (CODE: L, N) | | 9.5±1.0 | | |

* Carrier tape width 8mm.



For size 42 (1808) or over, Tape width 12mm and W₁: 14±1.5, W₂: 18.4mm max.

F=2mm (03, 05, 105 Type)





03 Type: 0.5 max.
05 Type: 0.75 max.
105 Type: 1.1 max.

F=4mm (105, D11, D12, F12, 21, 316, 32, 42, 52 Type)




F=8mm (43, 55 Type)



Bulk Cassette

(Unit: mm)



Carrier Tape

(Unit: mm)

| Type | A | B | F |
|----------------|-----------|-----------|----------|
| 03 (0.6×0.3) | 0.37±0.03 | 0.67±0.03 | 2.0±0.05 |
| 05 (1.0×0.5) | 0.65±0.1 | 1.15±0.1 | 2.0±0.05 |
| 105 (1.6×0.8) | 1.0±0.2 | 1.8±0.2 | 4.0±0.1 |
| D11 (1.37×1.0) | 1.15±0.2 | 1.55±0.2 | 4.0±0.1 |
| D12 (1.25×2.0) | 1.5±0.2 | 2.3±0.2 | 4.0±0.1 |
| F12 (1.25×2.0) | 1.5±0.2 | 2.3±0.2 | 4.0±0.1 |
| 21 (2.0×1.25) | 1.5±0.2 | 2.3±0.2 | 4.0±0.1 |
| 316 (3.2×1.6) | 2.0±0.2 | 3.6±0.2 | 4.0±0.1 |
| 32 (3.2×2.5) | 2.9±0.2 | 3.6±0.2 | 4.0±0.1 |
| 42 (4.5×2.0) | 2.4±0.2 | 4.9±0.2 | 4.0±0.1 |
| 43 (4.5×3.2) | 3.6±0.2 | 4.9±0.2 | 8.0±0.1 |
| 52 (5.7×2.0) | 2.4±0.2 | 6.0±0.2 | 4.0±0.1 |
| 55 (5.7×5.0) | 5.3±0.2 | 6.0±0.2 | 8.0±0.1 |

(Unit: mm)

| F | Carrier Tape | C | D | E | G | H | J |
|--------------|-----------------|--------------|--------------|--------------|--------------|-------------|----------------|
| 2.0 ±0.05 | 8mm Paper | 8.0 ±0.3 | 3.5 ±0.05 | | | | |
| 4.0 ±0.1 | 8mm Plastic | | | 1.75 ±0.1 | 2.0 ±0.05 | 4.0 ±0.1 | 1.5 +0.1/-0 |
| 8.0 ±0.1 | 12mm Plastic | 12.0 ±0.3 | 5.5 ±0.05 | | | | |


Circuit Design

1. Once application and assembly environments have been checked, the capacitor may be used in conformance with the rating and performance which are provided in both the catalog and the specifications. Use exceeding that which is specified may result in inferior performance or cause a short, open, smoking, or flaming to occur, etc.
2. Please consult the manufacturer in advance when the capacitor is used in devices such as: devices which deal with human life, i.e. medical devices; devices which are highly public orientated; and devices which demand a high standard of liability.
Accident or malfunction of devices such as medical devices, space equipment and devices having to do with atomic power could generate grave consequence with respect to human lives or, possibly, a portion of the public. Capacitors used in these devices may require high reliability design different from that of general purpose capacitors.
3. Please use the capacitors in conformance with the operating temperature provided in both the catalog and the specifications.
Be especially cautious not to exceed the maximum temperature. In the situation the maximum temperature set forth in both the catalog and specifications is exceeded, the capacitor's insulation resistance may deteriorate, power may suddenly surge and short-circuit may occur. The capacitor has a loss, and may self-heat due to equivalent series resistance when alternating electric current is passed therethrough. As this effect becomes especially pronounced in high frequency circuits, please exercise caution.
When using the capacitor in a (self-heating) circuit, please make sure the surface of the capacitor remains under the maximum temperature for usage. Also, please make certain temperature rises remain below 20°C.
4. Please keep voltage under the rated voltage which is applied to the capacitor. Also, please make certain the peak voltage remains below the rated voltage when AC voltage is super-imposed to the DC voltage.
In the situation where AC or pulse voltage is employed, ensure average peak voltage does not exceed the rated voltage.
Exceeding the rated voltage provided in both catalog and specifications may lead to defective withstanding voltage or, in worst case situations, may cause the capacitor to smoke or flame.
5. When the capacitor is to be employed in a circuit in which there is continuous application of a high frequency voltage or a steep pulse voltage, even though it is within the rated voltage, please inquire to the manufacturer.
In the situation the capacitor is to be employed using a high frequency AC voltage or a extremely fast rising pulse voltage, even though it is within the rated voltage, it is possible capacitor reliability will deteriorate.
6. It is a common phenomenon of high-dielectric products to have a deteriorated amount of static electricity due to the application of DC voltage. Due caution is necessary as the degree of deterioration varies depending on the quality of capacitor materials, capacity, as well as the load voltage at the time of operation.
7. Do not use the capacitor in an environment where it might easily exceed the respective provisions concerning shock and vibration specified in the catalog and specifications.
In addition, it is a common piezo phenomenon of high dielectric products to have some voltage due to vibration or to have noise due to voltage change. Please contact sales in such case.
8. If the electrostatic capacity value of the delivered capacitor is within the specified tolerance, please consider this when designing the respective product in order that the assembled product function appropriately.
9. Please contact us upon using conductive adhesives.

Storage

1. If the component is stored in minimal packaging (a heat-sealed or chuck-type plastic bag), the bag should be kept closed. Once the bag has been opened, reseal it or store it in a desiccator.
2. Keep storage place temperature +5 to +35 degree C, humidity 45 to 70% RH.
3. The storage atmosphere must be free of gas containing sulfur and chlorine. Also, avoid exposing the product to saline moisture. If the product is exposed to such atmospheres, the terminals will oxidize and solderability will be effected.
4. Precautions 1) to 3) apply to chip capacitors packaged in carrier tapes and bulk cases.
5. The solderability is assured for 12 months from our shipping date (six months for silver palladium) if the above storage precautions are followed.
6. Chip capacitors may crack if exposed to hydrogen (H₂) gas while sealed or if coated with silicon, which generates hydrogen gas.

Dimensions for recommended typical land



When mounting the capacitor to the substrate, it is important to consider carefully that the amount of solder (size of fillet) used has a direct effect upon the capacitor once it is mounted.

- The greater the amount of solder, the greater the stress to the elements. As this may cause the substrate to break or crack, it is important to establish the appropriate dimensions with regard to the amount of solder when designing the land of the substrate.
- In the situation where two or more devices are mounted onto a common land, separate the device into exclusive pads by using soldering resist.

Standard

(Unit: mm)

| Size | L×W | a | b | c |
|------|----------|--------------|--------------|--------------|
| 03 | 0.6×0.3 | 0.20 to 0.30 | 0.25 to 0.35 | 0.30 to 0.40 |
| 05 | 1.0×0.5 | 0.30 to 0.50 | 0.35 to 0.45 | 0.40 to 0.60 |
| 105 | 1.6×0.8 | 0.70 to 1.00 | 0.80 to 1.00 | 0.60 to 0.80 |
| 21 | 2.0×1.25 | 1.00 to 1.30 | 1.00 to 1.20 | 0.80 to 1.10 |
| 316 | 3.2×1.6 | 2.10 to 2.50 | 1.10 to 1.30 | 1.00 to 1.30 |
| 32 | 3.2×2.5 | 2.10 to 2.50 | 1.10 to 1.30 | 1.90 to 2.30 |
| 42 | 4.5×2.0 | 2.50 to 3.20 | 1.80 to 2.30 | 1.50 to 1.80 |
| 43 | 4.5×3.2 | 2.50 to 3.20 | 1.80 to 2.30 | 2.60 to 3.00 |
| 52 | 5.7×2.0 | 4.20 to 4.70 | 2.00 to 2.50 | 1.50 to 1.80 |
| 55 | 5.7×5.0 | 4.20 to 4.70 | 2.00 to 2.50 | 4.20 to 4.70 |


* CA series: Please refer applicable page.

Automotive Series

(Unit: mm)

| Size | L×W | a | b | c |
|------|----------|--------------|--------------|--------------|
| 105 | 1.6×0.8 | 0.60 to 0.90 | 0.80 to 1.00 | 0.70 to 1.00 |
| 21 | 2.0×1.25 | 0.90 to 1.20 | 0.80 to 1.20 | 0.90 to 1.40 |
| 316 | 3.2×1.6 | 1.40 to 1.90 | 1.00 to 1.30 | 1.30 to 1.80 |

Ideal Solder Thickness



Typical mounting problems

| Item | Not recommended example | Recommended example/ Separated by solder |
|-------------------------------|-------------------------|--|
| Multiple parts mount | | |
| Mount with leaded parts | | |
| Wire soldering after mounting | | |
| Overview | | |

Mounting Design

The chip could crack if the PCB warps during processing after the chip has been soldered.

Recommended chip position on PCB to minimize stress from PCB warpage



Actual Mounting

- 1) If the position of the vacuum nozzle is too low, a large force may be applied to the chip capacitor during mounting, resulting in cracking.
- 2) During mounting, set the nozzle pressure to a static load of 100 to 300 gf.
- 3) To minimize the shock of the vacuum nozzle, provide a support pin on the back of the PCB to minimize PCB flexure.



- 4) Bottom position of pick up nozzle should be adjusted to the top surface of a substrate which camber is corrected.
- 5) To reduce the possibility of chipping and cracks, minimize vibration to chips stored in a bulk case.
- 6) The discharge pressure must be adjusted to the part size. Verify the pressure during setup to avoid fracturing or cracking the chips capacitors.

Resin Mold


- 1) If a large amount of resin is used for molding the chip, cracks may occur due to contraction stress during curing. To avoid such cracks, use a low shrinkage resin.
- 2) The insulation resistance of the chip will degrade due to moisture absorption. Use a low moisture absorption resin.
- 3) Check carefully that the resin does not generate a decomposition gas or reaction gas during the curing process or during normal storage. Such gases may crack the chip capacitor or damage the device itself.

Soldering Method

- 1) Ceramic is easily damaged by rapid heating or cooling. If some heat shock is unavoidable, preheat enough to limit the temperature difference (Delta T) to within 130 degree Celsius.
- 2) The product size 1.0×0.5mm to 3.2×1.6mm can be used in reflow and wave soldering, and the product size of over 3.2×2.5mm, 0.6×0.3mm, and capacitor arrays can be used in reflow.
Circuit shortage and smoking can be created by using capacitors which are used neglecting the above caution.
- 3) Please see our recommended soldering conditions.
- 4) In case of using Sn-Zn Solder, please contact us in advance.


Recommended Temperature Profile (62Sn Solder)

Reflow



- ① Minimize soldering time.
- ② Ensure that allowable temperature difference does not exceed 150°C.
- ③ Ensure that allowable temperature difference does not exceed 130°C for 3.2×2.5mm size or larger.


Wave



- ① Ensure that the chip capacitor is preheated adequately.
- ② Ensure that the temperature difference (ΔT) does not exceed 150°C.
- ③ Cool naturally after soldering.
- ④ Wave soldering is not applicable for chips with size of 3.2×2.5mm or larger.


Recommended Temperature Profile (Sn-3Ag-0.5Cu)

Reflow



- ① Minimize soldering time.
- ② Ensure that allowable temperature difference does not exceed 150°C.
- ③ Ensure that allowable temperature difference does not exceed 130°C for 3.2×2.5mm size or larger.

Wave



- ① Ensure that the chip capacitor is preheated adequately.
- ② Ensure that the temperature difference (ΔT) does not exceed 150°C.
- ③ Cool naturally after soldering.
- ④ Wave soldering is not applicable for chips with size of 3.2×2.5mm or larger.

Soldering iron

- 1) Temperature of iron chip 380°C max.
- 2) Wattage 80W max.
- 3) Tip shape of soldering iron ϕ 3.0mm max.
- 4) Soldering Time 3 sec. max.

5) Cautions

- a) Pre-heating is necessary Rapid heating must be avoided.
Delta T ≤ 150°C
- b) Avoid direct touching to capacitors.
- c) Avoid rapid cooling after soldering. Natural cooling is recommended.