	Performance	Test condition
External Visual	No abnormal exterior appearance	Microscope ('10)
Physical Dimension	Within the specified dimensions	Using The calipers
Mechanical Shock	Appearance : No abnormal exterior appearance	Three shocks in each direction should be applied along
	Capacitance Change Within ±10 %	3 mutually perpendicular axes of the test specimen (18 shocks)
	Tan δ, IR : Initial spec.	Peak value Duration Wave Velocity
		1,500G 0.5ms Half sine 4.7m/sec
		Initial Measurement 2*
		Final Measurement 5*
Vibration	Appearance : No abnormal exterior appearance	5g's for 20min., 12cycles each of 3 orientations,
	Capacitance Change Within ±10 %	Use 8"×5" PCB 0.031" Thick 7 secure points on one long side
	Tan δ, IR : Initial spec.	and 2 secure points at corners of opposite sides. Parts mounted
		within 2" from any secure point. Test from 10~2,000Hz.
		Initial Measurement 2*
		Final Measurement 5*
Resistance to	Appearance : No abnormal exterior appearance	preheating : 150°C for 60~120 sec.
Solder Heat	Capacitance Change Within ±10 %	Solder pot : 260±5°C, 10±1sec.
	Tan δ, IR : Initial spec.	Initial Measurement 2*
		Final Measurement 3*
ESD	Appearance : No abnormal exterior appearance	AEC-Q200-002 or ISO/DIS10605
	Capacitance Change Within ±10 %	Initial Measurement 2*
	Tan δ, IR : Initial spec.	Final Measurement 4*
Solderability	95% of the terminations is to be soldered	a) Preheat at 155 $^{\circ}\!$
	evenly and continuously	b) Steam aging for 8 hours, Immerse in solder for 5s at 245±5℃
		c) Steam aging for 8 hours, Immerse in solder for 120s at 260±5 °C
		solder : a solution ethanol and rosin
Electrical	Capacitance : Within specified tolerance	*A capacitor prior to measuring the capacitance is heat treated at
Characterization	Tan δ:0.025 max.	150 +0/-10 ℃ for 1hour and maintained in ambient air for 24±2 hours
	IR(25℃): More than 10,000 ^{MΩ} or 500 ^{MΩ} ×μF	The Capacitance / D.F. should be measured at 25 ℃,
	Whichever is smaller	1 kHz \pm 10%, 1 \pm 0.2 Vrms
	IR(125℃) More than 1,000 ^{MΩ} or 10 ^{MΩ} ×μF	I.R. should be measured with a DC voltage not exceeding
	Whichever is smaller	Rated Voltage @25°C, @125°C for 60~120 sec.
	Dielectric Strength	Dielectric Strength : 200% of the rated voltage for 1~5 seconds
Board Flex	Appearance : No abnormal exterior appearance	Bending to the limit, 2 mm for 60 seconds 1*
	Capacitance Change Within ±10 %	Initial Measurement 2*
		Final Measurement 5*
Terminal	Appearance : No abnormal exterior appearance	18 N, for 60 sec.
Strength(SMD)	Capacitance Change Within ±10 %	Initial Measurement 2*
		Final Measurement 5*
Beam Load	Destruction value should be exceed 20 N	Beam speed: 0.5±0.05 mm/sec
Temperature	X7R	
Characteristics	From -55 °C to 125 °C, Capacitance change should be within ±15%	

D. Recommended Soldering method :

Reflow (Reflow Peak Temperature : 260 +0/-5°C, 30sec.), Meet IPC/JEDEC J-STD-020 D Standard

- *1 : The figure indicates typical specification. Please refer to individual specifications.
- *2 : Initial measurement : Perform a heat treatment at 150 +0/-10 $^\circ\!\!\mathrm{C}$ for one hour after soldering process. and then let sit for 24±2 hours at room temperature. Perform the initial measurement.
- $^{\star}3$: Final measurement : Let sit for 24 \pm 2 hours at room temperature after test conclusion, then measure.
- *4 : Final measurement : Perform a heat treatment at 150 +0/-10 °C for one hour after soldering process. and then let sit for 24±2 hours at room temperature. Perform the initial measurement.
- *5 : Final measurement : Let measure within 24 hours at room temperature after test conclusion.



A Product specifications included in the specifications are effective as of March 1, 2013.

Please be advised that they are standard product specifications for reference only.

We may change, modify or discontinue the product specifications without notice at any time.

So, you need to approve the product specifications before placing an order.

Should you have any question regarding the product specifications, please contact our sales personnel or application engineers.