

COG (NP0) Dielectric

Specifications and Test Methods



Parameter/Test		NPO Specification Limits	Measuring Conditions	
Operating Temperature Range		-55°C to +125°C	Temperature Cycle Chamber	
Capacitance		Within specified tolerance	Freq.: 1.0 MHz \pm 10% for cap \leq 1000 pF 1.0 kHz \pm 10% for cap $>$ 1000 pF Voltage: 1.0Vrms \pm .2V	
Q		$<$ 30 pF: $Q \geq 400+20 \times$ Cap Value \geq 30 pF: $Q \geq 1000$		
Insulation Resistance		100,000M Ω or 1000M Ω - μ F, whichever is less	Charge device with rated voltage for 60 \pm 5 secs @ room temp/humidity	
Dielectric Strength		No breakdown or visual defects	Charge device with 250% of rated voltage for 1-5 seconds, w/charge and discharge current limited to 50 mA (max) Note: Charge device with 150% of rated voltage for 500V devices.	
Resistance to Flexure Stresses	Appearance	No defects		
	Capacitance Variation	\pm 5% or \pm .5 pF, whichever is greater		
	Q	Meets Initial Values (As Above)		
	Insulation Resistance	\geq Initial Value \times 0.3		
Solderability		\geq 95% of each terminal should be covered with fresh solder	Dip device in eutectic solder at 230 \pm 5°C for 5.0 \pm 0.5 seconds	
Resistance to Solder Heat	Appearance	No defects, $<$ 25% leaching of either end terminal	Dip device in eutectic solder at 260°C for 60sec- onds. Store at room temperature for 24 \pm 2hours before measuring electrical properties.	
	Capacitance Variation	\leq \pm 2.5% or \pm .25 pF, whichever is greater		
	Q	Meets Initial Values (As Above)		
	Insulation Resistance	Meets Initial Values (As Above)		
	Dielectric Strength	Meets Initial Values (As Above)		
Thermal Shock	Appearance	No visual defects	Step 1: -55°C \pm 2°	30 \pm 3 minutes
	Capacitance Variation	\leq \pm 2.5% or \pm .25 pF, whichever is greater	Step 2: Room Temp	\leq 3 minutes
	Q	Meets Initial Values (As Above)	Step 3: +125°C \pm 2°	30 \pm 3 minutes
	Insulation Resistance	Meets Initial Values (As Above)	Step 4: Room Temp	\leq 3 minutes
	Dielectric Strength	Meets Initial Values (As Above)	Repeat for 5 cycles and measure after 24 hours at room temperature	
Load Life	Appearance	No visual defects	Charge device with twice rated voltage in test chamber set at 125°C \pm 2°C for 1000 hours (+48, -0). Remove from test chamber and stabilize at room temperature for 24 hours before measuring.	
	Capacitance Variation	\leq \pm 3.0% or \pm .3 pF, whichever is greater		
	Q (C=Nominal Cap)	\geq 30 pF: $Q \geq 350$ \geq 10 pF, $<$ 30 pF: $Q \geq 275 +5C/2$ $<$ 10 pF: $Q \geq 200 +10C$		
	Insulation Resistance	\geq Initial Value \times 0.3 (See Above)		
Load Humidity	Appearance	No visual defects	Store in a test chamber set at 85°C \pm 2°C/ 85% \pm 5% relative humidity for 1000 hours (+48, -0) with rated voltage applied. Remove from chamber and stabilize at room temperature for 24 \pm 2 hours before measuring.	
	Capacitance Variation	\leq \pm 5.0% or \pm .5 pF, whichever is greater		
	Q	\geq 30 pF: $Q \geq 350$ \geq 10 pF, $<$ 30 pF: $Q \geq 275 +5C/2$ $<$ 10 pF: $Q \geq 200 +10C$		
	Insulation Resistance	\geq Initial Value \times 0.3 (See Above)		
	Dielectric Strength	Meets Initial Values (As Above)		


COG (NP0) Dielectric

Capacitance Range



PREFERRED SIZES ARE SHADED

SIZE	0101*			0201			0402			0603				0805					1206										
	Reflow Only			Reflow Only			Reflow/Wave			Reflow/Wave				Reflow/Wave					Reflow/Wave										
Packaging	All Paper			All Paper			All Paper			All Paper				Paper/Embossed					Paper/Embossed										
(L) Length	0.40 ± 0.02 (0.016 ± 0.0008)			0.60 ± 0.09 (0.024 ± 0.004)			1.00 ± 0.10 (0.040 ± 0.004)			1.60 ± 0.15 (0.063 ± 0.006)				2.01 ± 0.20 (0.079 ± 0.008)					3.20 ± 0.20 (0.126 ± 0.008)										
W) Width	0.20 ± 0.02 (0.008 ± 0.0008)			0.30 ± 0.09 (0.011 ± 0.004)			0.50 ± 0.10 (0.020 ± 0.004)			0.81 ± 0.15 (0.032 ± 0.006)				1.25 ± 0.20 (0.049 ± 0.008)					1.60 ± 0.20 (0.063 ± 0.008)										
(t) Terminal	0.10 ± 0.04 (0.004 ± 0.0016)			0.15 ± 0.05 (0.006 ± 0.002)			0.25 ± 0.15 (0.010 ± 0.006)			0.35 ± 0.15 (0.014 ± 0.006)				0.50 ± 0.25 (0.020 ± 0.010)					0.50 ± 0.25 (0.020 ± 0.010)										
WVDC	16			25 50			16 25 50			16 25 50 100 200				16 25 50 100 200 250					16 25 50 100 200 250 500										
Cap (pF)	0.5			A	A	C	C	C	G	G	G	G			J	J	J	J	J			J	J	J	J	J	J		
	1.0	B		A	A	C	C	C	G	G	G	G			J	J	J	J	J			J	J	J	J	J	J		
	1.2	B		A	A	C	C	C	G	G	G	G			J	J	J	J	J			J	J	J	J	J	J		
	1.5	B		A	A	C	C	C	G	G	G	G			J	J	J	J	J			J	J	J	J	J	J		
	1.8	B		A	A	C	C	C	G	G	G	G			J	J	J	J	J			J	J	J	J	J	J		
	2.2	B		A	A	C	C	C	G	G	G	G			J	J	J	J	J			J	J	J	J	J	J		
2.7	B		A	A	C	C	C	G	G	G	G			J	J	J	J	J			J	J	J	J	J	J			
3.3	B		A	A	C	C	C	G	G	G	G			J	J	J	J	J			J	J	J	J	J	J			
3.9	B		A	A	C	C	C	G	G	G	G			J	J	J	J	J			J	J	J	J	J	J			
4.7	B		A	A	C	C	C	G	G	G	G			J	J	J	J	J			J	J	J	J	J	J			
5.6	B		A	A	C	C	C	G	G	G	G			J	J	J	J	J			J	J	J	J	J	J			
6.8	B		A	A	C	C	C	G	G	G	G			J	J	J	J	J			J	J	J	J	J	J			
8.2	B		A	A	C	C	C	G	G	G	G			J	J	J	J	J			J	J	J	J	J	J			
10	B		A	A	C	C	C	G	G	G	G			J	J	J	J	J	N		J	J	J	J	J	J			
12	B		A	A	C	C	C	G	G	G	G			J	J	J	J	J	N		J	J	J	J	J	J			
15	B		A	A	C	C	C	G	G	G	G			J	J	J	J	J	N		J	J	J	J	J	J			
18	B		A	A	C	C	C	G	G	G	G			J	J	J	J	J	N		J	J	J	J	J	J			
22	B		A	A	C	C	C	G	G	G	G			J	J	J	J	J	N		J	J	J	J	J	J			
27	B		A	A	C	C	C	G	G	G	G			J	J	J	J	J	N		J	J	J	J	J	J			
33	B		A	A	C	C	C	G	G	G	G			J	J	J	J	J	N		J	J	J	J	J	J			
39	B		A	A	C	C	C	G	G	G	G			J	J	J	J	J	N		J	J	J	J	J	J			
47	B		A	A	C	C	C	G	G	G	G			J	J	J	J	J	N		J	J	J	J	J	J			
56	B		A	A	C	C	C	G	G	G	G			J	J	J	J	J	N		J	J	J	J	J	J			
68	B		A	A	C	C	C	G	G	G	G			J	J	J	J	J	N		J	J	J	J	J	J			
82	B		A	A	C	C	C	G	G	G	G			J	J	J	J	J	N		J	J	J	J	J	J			
100	B		A	A	C	C	C	G	G	G	G			J	J	J	J	J	N		J	J	J	J	J	J			
120															J	J	J	J	N		J	J	J	J	J	J			
150															J	J	J	J	N		J	J	J	J	J	J			
180															J	J	J	J	N		J	J	J	J	J	J			
220															J	J	J	J	N		J	J	J	J	J	J			
270															J	J	J	J	N		J	J	J	J	J	J			
330															J	J	J	J	N		J	J	J	J	J	J			
390															J	J	J	J	N		J	J	J	J	J	J			
470															J	J	J	J	N		J	J	J	J	J	J			
560															J	J	J	J	N		J	J	J	J	J	J			
680															J	J	J	J	N		J	J	J	J	J	J			
820															J	J	J	J	N		J	J	J	J	J	J			
1000															J	J	J	J	N		J	J	J	J	J	J			
1200															J	J	J	J	N		J	J	J	J	J	J			
1500															J	J	J	J	N		J	J	J	J	J	J			
1800															J	J	J	J	N		J	J	J	J	J	J			
2200															N	N	N	N	N		J	J	J	M	M	Q			
2700															N	N	N	N	N		J	J	J	M	P	Q			
3300															P	N	N	N	N		J	J	M	P	Q				
3900															P	P	P	N	N		J	J	M	P					
4700															P	P	P	N	N		J	J	M	P					
5600															P	P	P	N	N		J	J	M	P					
6800															P	P	P	N	N		M	M	M	P					
8200															P	P	P	N	N		M	M	M	P					
Cap (μF)	0.010														P	P	P	N	N		P	P	P	P					
	0.012														P	P	P	N	N										
	0.015														P	P	P	N	N										
	0.018														P	P	P	N	N										
	0.022														P	P	P	N	N										
	0.027														P	P	P	N	N										
	0.033																												
	0.039																												
	0.047																												
	0.068																												
	0.082																												
	0.1																												
WVDC	16	25	50	16	25	50	16	25	50	100	200	16	25	50	100	200	250	16	25	50	100	200	250	500					
SIZE	0101*	0201	0402	0603	0805	1206																							



Letter	A	B	C	E	G		K	M	N	P	Q	X	Y	Z
Max. Thickness	0.33 (0.013)	0.22 (0.009)	0.56 (0.022)	0.71 (0.028)	0.90 (0.035)	0.94 (0.037)	1.02 (0.040)	1.27 (0.050)	1.40 (0.05 5)	1.52 (0.060)	1.78 (0.070)	2.29 (0.090)	2.54 (0.100)	2.79 (0.110)
	PAPER						EMBOSSD							




COG (NP0) Dielectric Capacitance Range



PREFERRED SIZES ARE SHADED



SIZE	1210					1812					1825				2220			2225		
Soldering	Reflow Only					Reflow Only					Reflow Only				Reflow Only			Reflow Only		
Packaging	Paper/Embossed					All Embossed					All Embossed				All Embossed			All Embossed		
(L) Length	3.20 ± 0.20 (0.126 ± 0.008)					4.50 ± 0.30 (0.177 ± 0.012)					4.50 ± 0.30 (0.177 ± 0.012)				5.70 ± 0.40 (0.225 ± 0.016)			5.72 ± 0.25 (0.225 ± 0.010)		
(W) Width	2.50 ± 0.20 (0.098 ± 0.008)					3.20 ± 0.20 (0.126 ± 0.008)					6.40 ± 0.40 (0.252 ± 0.016)				5.00 ± 0.40 (0.197 ± 0.016)			6.35 ± 0.25 (0.250 ± 0.010)		
(t) Terminal	0.50 ± 0.25 (0.020 ± 0.010)					0.61 ± 0.36 (0.024 ± 0.014)					0.61 ± 0.36 (0.024 ± 0.014)				0.64 ± 0.39 (0.025 ± 0.015)			0.64 ± 0.39 (0.025 ± 0.015)		
WVDC	25	50	100	200	500	25	50	100	200	500	50	100	200	50	100	200	50	100	200	
Cap (pF)	0.5																			
1.0																				
1.2																				
1.5																				
1.8																				
2.2																				
2.7																				
3.3																				
3.9																				
4.7																				
5.6																				
6.8																				
8.2																				
10					J															
12					J															
15					J															
18					J															
22					J															
27					J															
33					J															
39					J															
47					J															
56					J															
68					J															
82					J															
100					J															
120					J															
150					J															
180					J															
220					J															
270					J															
330					J															
390					M															
470					M															
560	J	J	J	J	M															
680	J	J	J	K	P															
820	J	J	J	K	P															
1000	J	J	P	P	P	K	K	N	N	M	M	M	M				M	M	P	
1200	P	P	P	P	P	K	K	N	N	M	M	M	M				M	M	P	
1500	P	P	P	P	P	K	K	N	N	M	M	M	M				M	M	P	
1800	P	P	P	P	P	K	K	N	N	M	M	M	M				M	M	P	
2200	P	P	P	P	N	K	K	N	N	P	X	X	M				M	M	P	
2700	P	P	P	P		K	K	N	P	Q	X	X	M				M	M	P	
3300	P	P	P	P		K	K	N	P	Q	X	X	X			X	M	M	P	
3900	P	P	P	P		K	K	N	P	Q	X	X	X			X	M	M	P	
4700	P	P	P			K	K	N	P	Y	X	X	X	X	X	X	M	M	P	
5600	P	P	P			K	K	P	P	Y	X	X	X	X	X	X	M	M	P	
6800	P	P	P			K	K	Q	Q		X	X	X	X	X	X	M	M	P	
8200	P	P				K	M	Q	Q		X	X	X	X	X	X	M	M	P	
Cap (pF)	0.010	N	N			K	M	Q	Q		X	X	X	X	X	X	M	M	P	
0.012	N	N				K	M	Q			X	X	X	X	X	X	M	M	P	
0.015						P	P	Q			X	X	X	X	X	X	M	M	Y	
0.018						P	P	Q			X	X	X	X	X	X	M	M	Y	
0.022						P	P	Q			X	X	X	X	X	X	M	Y	Y	
0.027						Q	Q	X			X	X	Y	X	X	X	P	Y	Y	
0.033						Q	Q	X			X	X		X	X		X	Y	Y	
0.039						X	X	X			X			Y			X	Y	Y	
0.047						X	X	X			X			Y			X	Z		
0.068						Z	Z	Y						Z			X	Z		
0.082						Z	Z	Y						Z			X	Z		
0.1						Z	Z	Z						Z			Z	Z		
WVDC	25	50	100	200	500	25	50	100	200	500	50	100	200	50	100	200	50	100	200	
SIZE	1210					1812					1825				2220			2225		



Letter	A	B	C	E	G	0.94	K	M	N	P	Q	X	Y	Z
Max. Thickness	0.33 (0.013)	0.22 (0.009)	0.56 (0.022)	0.71 (0.028)	0.90 (0.035)	0.94 (0.037)	1.02 (0.040)	1.27 (0.050)	1.40 (0.055)	1.52 (0.060)	1.78 (0.070)	2.29 (0.090)	2.54 (0.100)	2.79 (0.110)
PAPER							EMBOSSED							