


C0G (NP0) Dielectric

Specifications and Test Methods



Parameter/Test		NP0 Specification Limits	Measuring Conditions	
Operating Temperature Range		-55°C to +125°C	Temperature Cycle Chamber	
Capacitance		Within specified tolerance	Freq.: 1.0 MHz $\pm$ 10% for cap $\leq$ 1000 pF 1.0 kHz $\pm$ 10% for cap > 1000 pF Voltage: 1.0Vrms $\pm$.2V	
Q		<30 pF: Q $\geq$ 400+20 x Cap Value $\geq$ 30 pF: Q $\geq$ 1000		
Insulation Resistance		100,000M Ω or 1000M Ω - μ F, whichever is less	Charge device with rated voltage for 60 $\pm$ 5 secs @ room temp/humidity	
Dielectric Strength		No breakdown or visual defects	Charge device with 250% of rated voltage for 1-5 seconds, w/charge and discharge current limited to 50 mA (max) Note: Charge device with 150% of rated voltage for 500V devices.	
Resistance to Flexure Stresses	Appearance	No defects	Deflection: 2mm Test Time: 30 seconds 	
	Capacitance Variation	$\pm$ 5% or $\pm$ 5 pF, whichever is greater		
	Q	Meets Initial Values (As Above)		
	Insulation Resistance	$\geq$ Initial Value x 0.3		
Solderability		$\geq$ 95% of each terminal should be covered with fresh solder	Dip device in eutectic solder at 230 $\pm$ 5°C for 5.0 $\pm$ 0.5 seconds	
Resistance to Solder Heat	Appearance	No defects, <25% leaching of either end terminal	Dip device in eutectic solder at 260°C for 60sec- onds. Store at room temperature for 24 $\pm$ 2hours before measuring electrical properties.	
	Capacitance Variation	$\leq$ $\pm$ 2.5% or $\pm$.25 pF, whichever is greater		
	Q	Meets Initial Values (As Above)		
	Insulation Resistance	Meets Initial Values (As Above)		
	Dielectric Strength	Meets Initial Values (As Above)		
Thermal Shock	Appearance	No visual defects	Step 1: -55°C $\pm$ 2°	30 $\pm$ 3 minutes
	Capacitance Variation	$\leq$ $\pm$ 2.5% or $\pm$.25 pF, whichever is greater	Step 2: Room Temp	$\leq$ 3 minutes
	Q	Meets Initial Values (As Above)	Step 3: +125°C $\pm$ 2°	30 $\pm$ 3 minutes
	Insulation Resistance	Meets Initial Values (As Above)	Step 4: Room Temp	$\leq$ 3 minutes
	Dielectric Strength	Meets Initial Values (As Above)	Repeat for 5 cycles and measure after 24 hours at room temperature	
Load Life	Appearance	No visual defects	Charge device with twice rated voltage in test chamber set at 125°C $\pm$ 2°C for 1000 hours (+48, -0). Remove from test chamber and stabilize at room temperature for 24 hours before measuring.	
	Capacitance Variation	$\leq$ $\pm$ 3.0% or $\pm$.3 pF, whichever is greater		
	Q (C=Nominal Cap)	$\geq$ 30 pF: Q $\geq$ 350 $\geq$ 10 pF, <30 pF: Q $\geq$ 275 +5C/2 <10 pF: Q $\geq$ 200 +10C		
	Insulation Resistance	$\geq$ Initial Value x 0.3 (See Above)		
	Dielectric Strength	Meets Initial Values (As Above)		
Load Humidity	Appearance	No visual defects	Store in a test chamber set at 85°C $\pm$ 2°C/ 85% $\pm$ 5% relative humidity for 1000 hours (+48, -0) with rated voltage applied. Remove from chamber and stabilize at room temperature for 24 $\pm$ 2 hours before measuring.	
	Capacitance Variation	$\leq$ $\pm$ 5.0% or $\pm$.5 pF, whichever is greater		
	Q	$\geq$ 30 pF: Q $\geq$ 350 $\geq$ 10 pF, <30 pF: Q $\geq$ 275 +5C/2 <10 pF: Q $\geq$ 200 +10C		
	Insulation Resistance	$\geq$ Initial Value x 0.3 (See Above)		
	Dielectric Strength	Meets Initial Values (As Above)		

C0G (NP0) Dielectric

Capacitance Range



PREFERRED SIZES ARE SHADED

SIZE	0101*		0201		0402		0603					0805					1206						
Soldering	Reflow Only		Reflow Only		Reflow/Wave		Reflow/Wave					Reflow/Wave					Reflow/Wave						
Packaging	All Paper		All Paper		All Paper		All Paper					Paper/Embossed					Paper/Embossed						
L) Length	mm (in.)	0.40 ± 0.02 (0.016 ± 0.0008)	0.60 ± 0.09 (0.024 ± 0.004)		1.00 ± 0.10 (0.040 ± 0.004)		1.60 ± 0.15 (0.063 ± 0.006)					2.01 ± 0.20 (0.079 ± 0.008)					3.20 ± 0.20 (0.126 ± 0.008)						
W) Width	mm (in.)	0.20 ± 0.02 (0.008 ± 0.0008)	0.30 ± 0.09 (0.011 ± 0.004)		0.50 ± 0.10 (0.020 ± 0.004)		0.81 ± 0.15 (0.032 ± 0.006)					1.25 ± 0.20 (0.049 ± 0.008)					1.60 ± 0.20 (0.063 ± 0.008)						
t) Terminal	mm (in.)	0.10 ± 0.04 (0.004 ± 0.0016)	0.15 ± 0.05 (0.006 ± 0.002)		0.25 ± 0.15 (0.010 ± 0.006)		0.35 ± 0.15 (0.014 ± 0.006)					0.50 ± 0.25 (0.020 ± 0.010)					0.50 ± 0.25 (0.020 ± 0.010)						
	WVDC	16	25	50	16	25	50	16	25	50	100	200	16	25	50	100	200	16	25	50	100	200	500
Cap (pF)	0.5		A	A	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J
	1.0	B	A	A	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J
	1.2	B	A	A	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J
	1.5	B	A	A	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J
1.8	B	A	A	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J	J
	2.2	B	A	A	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J
	2.7	B	A	A	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J
3.3	B	A	A	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J	J
	3.9	B	A	A	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J
	4.7	B	A	A	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J
5.6	B	A	A	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J	J
	6.8	B	A	A	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J
	8.2	B	A	A	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J
10	B	A	A	C	C	C	G	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J
	12	B	A	A	C	C	C	G	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J
	15	B	A	A	C	C	C	G	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J
18	B	A	A	C	C	C	G	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J
	22	B	A	A	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J
	27	B	A	A	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J
33	B	A	A	C	C	C	G	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J
	39	B	A	A	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J
	47	B	A	A	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J
56	B	A	A	C	C	C	G	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J
	68	B	A	A	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J
	82	B	A	A	C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J
100	B	A	A	C	C	C	G	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J
	120				C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J
	150				C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J
180				C	C	C	G	G	G	G	G		J	J	J	J	J	J	J	J	J	J	J
	220				C	C	C	G	G	G	G	G	J	J	J	J	J	J	J	J	J	J	M
	270				C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	M
330				C	C	C	G	G	G	G	G		J	J	J	J	J	J	J	J	J	J	M
	390				C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	M
	470				C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	M
560				C	C	C	G	G	G	G	G		J	J	J	J	J	J	J	J	J	J	M
	680				C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	J	P
	820				C	C	C	G	G	G	G		J	J	J	J	J	J	J	J	J	M	
1000				C	C	C	G	G	G	G	G		J	J	J	J	J	J	J	J	J	Q	
	1200						G	G	G	G			J	J	J	J	J	J	J	J	J	Q	
	1500						G	G	G	G			J	J	J	J	J	J	J	J	M	Q	
1800							G	G	G	G			J	J	J	N		J	J	M	M	Q	
	2200						G	G	G	G			N	N	N	N		J	J	M	P	Q	
	2700						G	G	G	G			N	N	N	N		J	J	M	P	Q	
3300							G	G	G	G			P	P	P	N		J	J	M	P	Q	
	3900						G	G	G	G			P	P	P	N		J	J	M	P		
	4700						G	G	G	G			P	P	P	N		J	J	M	P		
5600													P	P	P			J	J	M	P		
	6800												P	P	P			M	M	M	P		
	8200												P	P	P			M	M	M	P		
Cap (μF)	0.010												P	P	P			P	P	P	P		
	0.012																						
	0.015																						
0.018																							
	0.022																						
	0.027																						
0.033																							
	0.039																						
	0.047																						
0.068																							
	0.082																						
	0.1																						
WVDC	16	25	50	16	25	50	16	25	50	100	200	16	25	50	100	200	16	25	50	100	200	500	
SIZE	0101*	0201		0402		0603					0805					1206							
Letter	A	B	C	E	G	J	K	M	N	P	Q	X	Y	Z									
Max. Thickness	0.33 (0.013)	0.22 (0.009)	0.56 (0.022)	0.71 (0.028)	0.90 (0.035)	0.94 (0.037)	1.02 (0.040)	1.27 (0.050)	1.40 (0.055)	1.52 (0.060)	1.78 (0.070)	2.29 (0.090)	2.54 (0.100)	2.79 (0.110)									
	PAPER						EMBOSS																

PAPER and EMBOSS available for 01005

C0G (NP0) Dielectric



Capacitance Range

PREFERRED SIZES ARE SHADED

SIZE		1210					1812					1825				2220				2225			
Soldering		Reflow Only					Reflow Only					Reflow Only				Reflow Only				Reflow Only			
Packaging		Paper/Embossed					All Embossed					All Embossed				All Embossed				All Embossed			
(L) Length	mm	3.20 ± 0.20					4.50 ± 0.30					4.50 ± 0.30				5.70 ± 0.40				5.72 ± 0.25			
	(in.)	(0.126 ± 0.008)					(0.177 ± 0.012)					(0.177 ± 0.012)				(0.225 ± 0.016)				(0.225 ± 0.010)			
(W) Width	mm	2.50 ± 0.20					3.20 ± 0.20					6.40 ± 0.40				5.00 ± 0.40				6.35 ± 0.25			
	(in.)	(0.098 ± 0.008)					(0.126 ± 0.008)					(0.252 ± 0.016)				(0.197 ± 0.016)				(0.250 ± 0.010)			
(t) Terminal	mm	0.50 ± 0.25					0.61 ± 0.36					0.61 ± 0.36				0.64 ± 0.39				0.64 ± 0.39			
	(in.)	(0.020 ± 0.010)					(0.024 ± 0.014)					(0.024 ± 0.014)				(0.025 ± 0.015)				(0.025 ± 0.015)			
Cap (pF)	0.5	25	50	100	200	500	25	50	100	200	500	50	100	200	50	100	200	50	100	200			
	1.0																						
	1.2																						
	1.5																						
	1.8																						
	2.2																						
	2.7																						
	3.3																						
	3.9																						
	4.7																						
	5.6																						
	6.8																						
	8.2																						
	10					J																	
	12					J																	
	15					J																	
	18					J																	
	22					J																	
	27					J																	
	33					J																	
	39					J																	
	47					J																	
	56					J																	
	68					J																	
	82					J																	
	100					J																	
	120					J																	
	150					J																	
	180					J																	
	220					J																	
	270					J																	
	330					J																	
	390					M																	
	470					M																	
	560	J	J	J	J	M																	
	680	J	J	J	K	P																	
	820	J	J	J	K	P																	
	1000	J	J	P	P	P	K	K	N	N	M	M	M	M				M	M	P			
	1200	P	P	P	P	P	K	K	N	N	M	M	M	M				M	M	P			
	1500	P	P	P	P	P	K	K	N	N	M	M	M	M				M	M	P			
	1800	P	P	P	P	P	K	K	N	N	M	M	M	M				M	M	P			
	2200	P	P	P	P	N	K	K	N	N	P	X	X	M				M	M	P			
	2700	P	P	P	P		K	K	N	P	Q	X	X	M				M	M	P			
	3300	P	P	P	P		K	K	N	P	Q	X	X	X			X	M	M	P			
	3900	P	P	P			K	K	N	P	Q	X	X	X			X	M	M	P			
	4700	P	P	P			K	K	N	P	Y	X	X	X	X	X	X	M	M	P			
	5600	P	P	P			K	K	P	P	Y	X	X	X	X	X	X	M	M	P			
	6800	P	P	P			K	K	Q	Q		X	X	X	X	X	X	M	M	P			
	8200	P	P	P			K	M	Q	Q		X	X	X	X	X	X	M	M	P			
Cap (µF)	0.010	N	N				K	M	Q	Q		X	X	X	X	X	X	M	M	P			
	0.012	N	N				K	M	Q			X	X	X	X	X	X	M	M	P			
	0.015						P	P	Q			X	X	X	X	X	X	M	M	Y			
	0.018						P	P	Q			X	X	X	X	X	X	M	M	Y			
	0.022						P	P	Q			X	X	X	X	X	X	M	Y	Y			
	0.027						Q	Q	X			X	X	Y		X	X	P	Y	Y			
	0.033						Q	Q	X			X	X			X	X	X	Y	Y			
	0.039						X	X	X			X				Y		X	Y	Y			
	0.047						X	X	X			X				Y		X	Z				
	0.068						Z	Z	Y							Z		X	Z				
	0.082						Z	Z	Y							Z		X	Z				
	0.1						Z	Z	Z							Z		X	Z				
WVDC		25	50	100	200	500	25	50	100	200	500	50	100	200	50	100	200	50	100	200			
SIZE		1210					1812					1825				2220				2225			
Letter		A	B	C	E	G	J	K	M	N	P	Q	X	Y	Z								
Max. Thickness		0.33 (0.013)	0.22 (0.009)	0.56 (0.022)	0.71 (0.028)	0.90 (0.035)	0.94 (0.037)	1.02 (0.040)	1.27 (0.050)	1.40 (0.055)	1.52 (0.060)	1.78 (0.070)	2.29 (0.090)	2.54 (0.100)	2.79 (0.110)								
		PAPER					EMBOSSED																